

MODIFIED PARTICLE, CATALYST COMPONENT FOR ADDITION
POLYMERIZATION, CATALYST FOR ADDITION POLYMERIZATION AND
PROCESS FOR PRODUCING ADDITION POLYMER

5

BACKGROUND OF THE INVENTION

Technical Field

The present invention relates to a modified particle used
for a catalyst component for addition polymerization; a catalyst
component for addition polymerization; a catalyst for addition
10 polymerization obtained using the same; and a process for
producing an addition polymer.

Description of Related Arts

Olefin polymers such as polypropylene and polyethylene are
15 superior in mechanical properties and chemical resistance and
additionally superior in balance between properties and
economies, and thereby they are extensively used in various
molding fields.

These olefin polymers have hitherto been produced by
20 polymerizing an olefin mainly using a conventional solid
catalyst (multi-site catalyst) formed from a combination of
the 4 Group metal compound such as titanium trichloride or
titanium tetrachloride and the 13 Group metal compound typified
by an organoaluminum compound.

25 In recent years, there has been proposed a process for
producing an addition polymer comprising the step of
polymerizing an olefin and the like using a so-called single
site catalyst, which is a combination of a transition metal
compound (for example, a metallocene complex and a

non-metallocene complex) different from the solid catalyst component so far used, and an aluminoxane and the like. For example, a process comprising the step of using a combination of bis(cyclopentadienyl)zirconium dichloride and
5 methylaluminoxane is reported in JP-A 58-19309. In addition, a combination of such a transition metal compound and a specific boron compound is also reported. For example, a process comprising the step of using bis(cyclopentadienyl)zirconium dimethyl and tri(n-butyl)ammonium
10 tetrakis(pentafluorophenyl)borate is reported in JP-W1-502036. As known, an addition polymer obtained using such a single site catalyst is generally narrower in its molecular weight distribution than that obtained using the conventional solid catalyst (multi-site catalyst), and in the case of a copolymer,
15 an addition polymer more homogeneous than that obtained using the conventional solid catalyst can be obtained because the comonomers are more homogeneously copolymerized.

An improvement of such catalysts for addition polymerization has been studied intensively, and, the kinds
20 of metals used as a main catalyst component are broadly reported regarding each of Groups of the Periodic Table. For example, in Angew. Chem. Int. Ed. 38, 428(1999), it is reported that metallocene complexes and non-metallocene compounds of metals of the Groups 3 to 13 are effective as a main catalyst component.
25 On the other hand, as a co-catalyst component for activation used in combination of the metallocene complex or non-metallocene compound, aluminixanes and boron compounds belonging to the Group 13 occupy the center of its development. As a boron compound, a compound having an electron-withdrawing

group on the boron atom, is generally effective.

SUMMARY OF THE INVENTION

An object of the present invention is to provide a modified
5 particle which can form a catalyst for addition polymerization
exhibiting a high polymerization activity by using as a
co-catalyst component for activation(catalyst component); a
catalyst component for addition polymerization composed of the
modified particle; a catalyst for addition polymerization
10 prepared by using the catalyst component; and a process for
producing an addition polymer efficiently using the catalyst
for addition polymerization.

Namely, the present invention relates to a modified
particle (A) obtained by contacting the following (a), (b) and
15 (c); a catalyst component for addition polymerization
containing the modified particle; a catalyst for addition
polymerization prepared by contacting the modified particle(A)
and a transition metal compound of Groups 3 to 11 or lanthanide
series(B); and a catalyst for addition polymerization prepared
20 by contacting the modified particle(A), a transition metal
compound of Groups 3 to 11 or lanthanide series(B) and an
organoaluminum compound(C); and further to a process for
producing an addition polymer using these catalysts:

(a) a compound represented by the following formula [1],



(b) a compound represented by the following formula [2],



(c) particle,

wherein m is a numeral corresponding to a valence of Bi; L^1

is a hydrogen atom, a halogen atom, a hydrocarbon group or a hydrocarbon oxy group, when more than one L^1 exist, they may be the same or different from one another; R^1 is an electron-withdrawing group or an electron-withdrawing group-containing group, when more than one R^1 exists, they may be the same or different from one another ; T represents a non-metal atom of Group 15 or 16 of the periodic table; t is a numeral corresponding to a valence of T; n is an integer of 1 to t excluding 2.

Further, the present invention relates to a catalyst component for addition polymerization composed of the modified particle (A).

Still further, the present invention relates to a catalyst for addition polymerization obtained by contacting the modified particle (A) with a transition metal compound (B) of Group 3-11 or lanthanide series, and optionally an organoaluminum compound (C).

Furthermore, the present invention relates to a process for producing an addition polymer which comprises polymerizing an addition-polymerizable monomer with the catalyst for addition polymerization described above.

The present invention will be explained in more detail below.

DETAILED DESCRIPTION OF THE INVENTION

In the above formula [1], m represents a valence of Bi, and is 3 or 5, preferably 3.

L^1 in the above formula [1] represents a hydrogen atom, a halogen atom, a hydrocarbon group or a hydrocarbon oxy group, and when more than one L^1 exists, they may be the same or different

from one another. Specific examples of the halogen atom as L¹ include a fluorine atom, a chlorine atom, a bromine atom and an iodine atom. As a hydrocarbon group as L¹, an alkyl group, an aryl group or an aralkyl group is preferred. As a hydrocarbon oxy group as L¹, an alkoxy group or an aryloxy group is preferred.

The alkyl group is preferably an alkyl group having 1 to 20 carbon atoms. Examples thereof include a methyl group, an ethyl group, a n-propyl group, an isopropyl group, a n-butyl group, a sec-butyl group, a tert-butyl group, an isobutyl group, a n-pentyl group, a neopentyl group, a n-hexyl group, a n-heptyl, a n-octyl group, a n-decyl group, a n-dodecyl group, a n-pentadecyl group and a n-eicosyl group. More preferred is a methyl group, an ethyl group, an isopropyl group, a tert-butyl group and an isobutyl group.

These alkyl groups may be substituted with a halogen atom such as a fluorine atom, a chlorine atom, a bromine atom or an iodine atom. Examples of the alkyl group having 1 to 20 carbon atoms substituted with the halogen atom include a fluoromethyl group, a difluoromethyl group, a trifluoromethyl group, a chloromethyl group, a dichloromethyl group, a trichloromethyl group, a bromomethyl group, a dibromomethyl group, a tribromomethyl group, an iodomethyl group, a diiodomethyl group, a triiodomethyl group, a fluoroethyl group, a difluoroethyl group, a trifluoroethyl group, a tetrafluoroethyl group, a pentafluoroethyl group, a chloroethyl group, a dichloroethyl group, a trichloroethyl group, a tetrachloroethyl group, a pentachloroethyl group, a bromoethyl group, a dibromoethyl group, a tribromoethyl group, a tetrabromoethyl group, a pentabromoethyl group, a perfluoropropyl group, a

perfluorobutyl group, a perfluoropentyl group, a
 perfluorohexyl group, a perfluorooctyl group, a
 perfluorododecyl group, a perfluoropentadecyl group, a
 perfluoroeicosyl group, a perchloropropyl group, a
 5 perchlorobutyl group, a perchloropentyl group, perchlorohexyl
 group, a perchlorooctyl group, a perchlorododecyl group, a
 perchloropentadecyl group, a perchloroeicosyl group, a
 perbromopropyl group, a perbromobutyl group, a perbromopentyl
 group, a perbromohexyl group, a perbromooctyl group, a
 10 perbromododecyl group, a perbromopentadecyl group and a
 perbromoeicosyl group, a 1H,1H-perfluoropropyl group, a
 1H,1H-perfluorobutyl group, a 1H,1H-perfluoropentyl group, a
 1H,1H-perfluorohexyl group, a 1H,1H-perfluorooctyl group, a
 1H,1H-perfluorododecyl group, a 1H,1H-perfluoropentadecyl
 15 group, a 1H,1H-perfluoroeicosyl group, a 1H,1H-perchloropropyl
 group, a 1H,1H-perchlorobutyl group, a 1H,1H-perchloropentyl
 group, a 1H,1H-perchlorohexyl group, a 1H,1H-perchlorooctyl
 group, a 1H,1H-perchlorododecyl group, a
 1H,1H-perchloropentadecyl group, a 1H,1H-perchloroeicosyl
 20 group, a 1H,1H-perbromopropyl group, a 1H,1H-perbromobutyl
 group, a 1H,1H-perbromopentyl group, a 1H,1H-perbromohexyl
 group, a 1H,1H-perbromooctyl group, a 1H,1H-perbromododecyl
 group, a 1H,1H-perbromopentadecyl group and a
 1H,1H-perbromoeicosyl group.

25 Further, these alkyl groups may be partially substituted
 with an alkoxy group such as a methoxy group or an ethoxy group,
 an aryloxy group such as a phenoxy group, or an aralkyloxy group
 such as a benzyloxy group.

The aryl group is preferably an aryl group having 6 to

20 carbon atoms. Examples thereof include a phenyl group, a 2-tolyl group, a 3-tolyl group, a 4-tolyl group, a 2,3-xylyl group, a 2,4-xylyl group, a 2,5-xylyl group, a 2,6-xylyl group, a 3,4-xylyl group, a 3,5-xylyl group, a 2,3,4-trimethylphenyl group, a 2,3,5-trimethylphenyl group, a 2,3,6-trimethylphenyl group, a 2,4,6-trimethylphenyl group, a 3,4,5-trimethylphenyl group, a 2,3,4,5-tetramethylphenyl group, a 2,3,4,6-tetramethylphenyl group, a 2,3,5,6-tetramethylphenyl group, a pentamethylphenyl group, an ethylphenyl group, a n-propylphenyl group, an isopropylphenyl group, a n-butylphenyl group, a sec-butylphenyl group, a tert-butylphenyl group, an isobutylphenyl group, a n-pentylphenyl group, a neopentylphenyl group, a n-hexylphenyl group, a n-octylphenyl group, a n-decylphenyl group, a n-dodecylphenyl group, a n-tetradecylphenyl group, a naphthyl group and an anthracenyl group, and more preferred is a phenyl group.

These aryl groups may be partially substituted with a halogen atom such as a fluorine atom, a chlorine atom, a bromine atom or an iodine atom, an alkoxy group such as a methoxy group or an ethoxy group, an aryloxy group such as a phenoxy group, or an aralkyloxy group such as a benzyloxy group.

The aralkyl group is preferably an aralkyl group having 7 to 20 carbon atoms. Examples thereof include a benzyl group, a (2-methylphenyl)methyl group, a (3-methylphenyl)methyl group, a (4-methylphenyl)methyl group, a (2,3-dimethylphenyl)methyl group, a (2,4-dimethylphenyl)methyl group, a (2,5-dimethylphenyl)methyl group, a (2,6-dimethylphenyl)methyl group, a

(3,4-dimethylphenyl)methyl group, a
 (3,5-dimethylphenyl)methyl group, a
 (2,3,4-trimethylphenyl)methyl group, a
 (2,3,5-trimethylphenyl)methyl group, a
 5 (2,3,6-trimethylphenyl)methyl group, a
 (3,4,5-trimethylphenyl)methyl group, a
 (2,4,6-trimethylphenyl)methyl group, a
 (2,3,4,5-tetramethylphenyl)methyl group, a
 (2,3,4,6-tetramethylphenyl)methyl group, a
 10 (2,3,5,6-tetramethylphenyl)methyl group, a
 (pentamethylphenyl)methyl group, an (ethylphenyl)methyl group,
 a (n-propylphenyl)methyl group, an (isopropylphenyl)methyl
 group, a (n-butylphenyl)methyl group, a
 (sec-butylphenyl)methyl group, a (tert-butylphenyl)methyl
 15 group, an (isobutylphenyl)methyl group, a
 (n-pentylphenyl)methyl group, a (neopentylphenyl)methyl group,
 a (n-hexylphenyl)methyl group, a (n-octylphenyl)methyl group,
 a (n-decylphenyl)methyl group, a naphthylmethyl group and an
 anthracenylmethyl group, and more preferred is a benzyl group.

20 These aralkyl groups may be partially substituted with
 a halogen atom such as a fluorine atom, a chlorine atom, a bromine
 atom or an iodine atom, an alkoxy group such as a methoxy group
 or an ethoxy group, an aryloxy group such as a phenoxy group,
 or an aralkyloxy group such as a benzyloxy group.

25 The alkoxy group is preferably an alkoxy group having 1
 to 20 carbon atoms. Examples thereof include a methoxy group,
 an ethoxy group, a n-propoxy group, an isopropoxy group, a
 n-butoxy group, a sec-butoxy group, a tert-butoxy group, an
 isobutoxy group, a n-pentyloxy group, a neopentyloxy group,

a n-hexyloxy group, a n-octyloxy group, a n-decyloxy group, a n-dodecyloxy group, a n-pentadecyloxy group, a n-eicosyl oxy group, and the like. A methoxy group, an ethoxy group, an isopropoxy group, a tert-butoxy group or an isobutoxy group
5 is more preferable.

These alkoxy groups may be partially substituted with a halogen atom such as a fluorine atom, a chlorine atom, a bromine atom or an iodine atom, an alkoxy group such as a methoxy group or an ethoxy group, an aryloxy group such as a phenoxy group,
10 or an aralkyloxy group such as a benzyloxy group.

The aryloxy group is preferably an aryloxy group having 6 to 20 carbon atoms, and specific examples thereof include for example, a phenoxy group, a 2-tolyloxy group, a 3-tolyloxy group, a 4-tolyloxy group, a 2,3-xylyloxy group, a 2,4-xylylphenoxy
15 group, a 2,5-xylyloxy group, a 2,6-xylyloxy group, a 3,4-xylyloxy group, a 3,5-xylyloxy group, a 2,3,4-trimethylphenoxy group, a 2,3,5-trimethylphenoxy group, a 2,3,6-trimethylphenoxy group, a 2,4,6-trimethylphenoxy group, a 3,4,5-trimethylphenoxy group, a 2,3,4,5-tetramethylphenoxy
20 group, a 2,3,4,6-tetramethylphenoxy group, 2,3,5,6-tetramethylphenoxy group, a pentamethylphenoxy group, an ethylphenoxy group, a n-propylphenoxy group, an isopropylphenoxy group, a n-butylphenoxy group, a sec-butylphenoxy group, a tert-butylphenoxy group, an
25 isobutylphenoxy, n-pentylphenoxy, a neopentylphenoxy, n-hexylphenoxy group, a n-octylphenoxy group, a n-decylphenoxy group, a n-tetradecylphenoxy group, a naphthoxy group, an anthrathenoxy group and the like. More preferred is a phenoxy group.

These alkoxy groups may be partially substituted with a halogen atom such as a fluorine atom, a chlorine atom, a bromine atom or an iodine atom, an alkoxy group such as a methoxy group or an ethoxy group, an aryloxy group such as a phenoxy group, or
5 an aralkyloxy group such as a benzyloxy group.

As L^1 in the above formula [1], preferred is a halogen atom, an alkyl group, an aryl group, alkoxy group or an aryloxy group, more preferred is a hydrogen atom, aryl group, alkoxy group or aryloxy group, and particularly preferable is an aryl
10 group.

The compound (b) is a compound represented in the formula [2].



T in the above formula [2] is a non-metal atom of Group
15 15 or Group 16 of the periodic table of elements (Revised edition of IUPAC Inorganic Chemistry Nomenclature 1989). Specific examples of the non-metal atom of the Group 15 include a nitrogen atom and a phosphorous atom, and specific examples of the non-metal atom of the Group 16 are an oxygen atom and a sulfur
20 atom. As T, a nitrogen atom or a oxygen atom is preferred. As T, particularly preferred is an oxygen atom.

"t" in the above-mentioned formula [2] is a numeral corresponding to a valence of T. For example, when T is a non-metal atom of the Group 15, t is 3, and when T is a non-metal atom
25 of the Group 16, t is 2.

"n" is an integer satisfying $1 \leq n \leq t$ but excludes 2 because when "n" is 2, it is difficult to obtain the effect of the present invention. "n" is preferably 1.

R^1 in the above-mentioned formula [2] is an

electron-withdrawing group or an electron-withdrawing group-containing group, and when more than one R^1 exist, they may be the same or different from one another. As an index of the electron-withdrawing property, there is known a substituent constant σ of the Hammett's rule. As the electron-withdrawing group, there is a functional group whose substituent constant σ of the Hammett's rule is positive.

Specific examples of the electron-withdrawing group include a fluorine atom, a chlorine atom, a bromine atom, an iodine atom, a cyano group, a nitro group, a carbonyl group, a sulfone group and a phenyl group. Examples of the electron-withdrawing group-containing group include a halogenated alkyl group, a halogenated aryl group, a (halogenated alkyl)aryl group, a cyanated aryl group, a nitrated aryl group and an ester group (for example, alkoxycarbonyl group, aralkyloxycarbonyl group and aryloxycarbonyl group), an acyl group, a halogenated acyl group and the like.

Specific examples of the halogenated alkyl group include a fluoromethyl group, a chloromethyl group, a bromomethyl group, an iodomethyl group, a difluoromethyl group, a dichloromethyl group, a dibromomethyl group, a diiodomethyl group, a trifluoromethyl group, a trichloromethyl group, a tribromomethyl group, a triiodomethyl group, a 2,2,2-trifluoroethyl group, a 2,2,2-trichloroethyl group, a 2,2,2-tribromoethyl group, a 2,2,2-triiodoethyl group, a 2,2,3,3,3-pentafluoropropyl group, a 2,2,3,3,3-pentachloropropyl group, a 2,2,3,3,3-pentabromopropyl group, a 2,2,3,3,3-pentaiodopropyl group, a

2,2,2-trifluoro-1-trifluoromethylethyl group, a
 2,2,2-trichloro-1-trichloromethylethyl group, a
 2,2,2-tribromo-1-tribromomethylethyl group, a
 2,2,2-triiodo-1-triiodomethylethyl group, a
 5 1,1-bis(trifluoromethyl)-2,2,2-trifluoroethyl group, a
 1,1-bis(trichloromethyl)-2,2,2-trichloroethyl group, a
 1,1-bis(tribromomethyl)-2,2,2-tribromoethyl group, a
 1,1-bis(triiodomethyl)-2,2,2-triiodoethyl group, a
 1H,1H-perfluorobutyl group, a 1H,1H-perfluoropentyl group, a
 10 1H,1H-perfluorohexyl group, a 1H,1H-perfluorooctyl group, a
 1H,1H-perfluorododecyl group, a 1H,1H-perfluoropentadecyl
 group, a 1H,1H-perfluoroeicosyl group, a 1H,1H-perchlorobutyl
 group, a 1H,1H-perchloropentyl group, a 1H,1H-perchlorohexyl
 group, a 1H,1H-perchlorooctyl group, a 1H,1H-perchlorododecyl
 15 group, a 1H,1H-perchloropentadecyl group, a
 1H,1H-perchloroeicosyl group, a 1H,1H-perbromobutyl group, a
 1H,1H-perbromopentyl group, a 1H,1H-perbromohexyl group, a
 1H,1H-perbromooctyl group, a 1H,1H-perbromododecyl group, a
 1H,1H-perbromopentadecyl group and a 1H,1H-perbromoeicosyl
 20 group.

Specific examples of the halogenated aryl group are a
 2-fluorophenyl group, a 3-fluorophenyl group, a 4-fluorophenyl
 group, a 2,4-difluorophenyl group, a 2,6-difluorophenyl group,
 a 3,4-difluorophenyl group, a 3,5-difluorophenyl group, a
 25 2,4,6-trifluorophenyl group, a 2,3,5,6-tetrafluorophenyl
 group, a pentafluorophenyl group, a
 2,3,5,6-tetrafluoro-4-trifluoromethylphenyl group, a
 2,3,5,6-tetrafluoro-4-pentafluorophenylphenyl group, a
 perfluoro-1-naphthyl group, a perfluoro-2-naphthyl group, a

2-chlorophenyl group, a 3-chlorophenyl group, a 4-chlorophenyl group, a 2,4-dichlorophenyl group, a 2,6-dichlorophenyl group, a 3,4-dichlorophenyl group, a 3,5-dichlorophenyl group, a 2,4,6-trichlorophenyl group, a 2,3,5,6-tetrachlorophenyl group, a pentachlorophenyl group, a 2,3,5,6-tetrachloro-4-trichloromethylphenyl group, a 2,3,5,6-tetrachloro-4-pentachlorophenylphenyl group, a perchloro-1-naphthyl group, a perchloro-2-naphthyl group, a 2-bromophenyl group, a 3-bromophenyl group, a 4-bromophenyl group, a 2,4-dibromophenyl group, a 2,6-dibromophenyl group, a 3,4-dibromophenyl group, a 3,5-dibromophenyl group, a 2,4,6-tribromophenyl group, a 2,3,5,6-tetrabromophenyl group, a pentabromophenyl group, a 2,3,5,6-tetrabromo-4-tribromomethylphenyl group, a 2,3,5,6-tetrabromo-4-pentabromophenylphenyl group, a perbromo-1-naphthyl group, a perbromo-2-naphthyl group, a 2-iodophenyl group, a 3-iodophenyl group, a 4-iodophenyl group, a 2,4-diiodophenyl group, a 2,6-diiodophenyl group, a 3,4-diiodophenyl group, a 3,5-diiodophenyl group, a 2,4,6-triiodophenyl group, a 2,3,5,6-tetraiodophenyl group, a pentaiodophenyl group, a 2,3,5,6-tetraiodo-4-triiodomethylphenyl group, a 2,3,5,6-tetraiodo-4-pentaiodophenylphenyl group, a periodo-1-naphthyl group and a periodo-2-naphthyl group.

Specific examples of the (halogenated alkyl)aryl group include a 2-(trifluoromethyl)phenyl group, a 3-(trifluoromethyl)phenyl group, a 4-(trifluoromethyl)phenyl group, a 2,6-bis(trifluoromethyl)phenyl group, a 3,5-bis(trifluoromethyl)phenyl group and a

2,4,6-tris(trifluoromethyl)phenyl group.

Specific examples of the cyanated aryl group include a 2-cyanophenyl group, a 3-cyanophenyl group and a 4-cyanophenyl group.

5 Specific examples of the nitrated aryl group include a 2-nitrophenyl group, a 3-nitrophenyl group and a 4-nitrophenyl group.

Specific examples of the ester group include a methoxycarbonyl group, an ethoxycarbonyl group, a
10 n-propoxycarbonyl group, an isopropoxycarbonyl group, a phenoxy carbonyl group, a trifluoromethoxycarbonyl group and a pentafluorophenoxy carbonyl group.

Specific examples of the acyl group include a formyl group, an ethanoyl group, a n-propopanoyl group, a butanoyl group,
15 a trifluoroethanoyl group, a benzoyl group, a pentafluorobenzoyl group, a perfluoroethanoyl group, a perfluoropropanoyl group, a perfluorobutanoyl group, a perfluoropentanoyl group, a perfluorohexanoyl group, a perfluoroheptanoyl group, a perfluorooctanoyl group, a
20 perfluorononanoyl group, a perfluorodecanoyl group, a perfluoroundecanoyl group and a perfluorododecanoyl group.

R^1 is preferably a halogenated hydrocarbon group, more preferably halogenated alkyl group and a halogenated aryl group. Further preferred is a fluoromethyl group, a difluoromethyl
25 group, a trifluoromethyl group, a 2,2,2-trifluoroethyl group, a 2,2,3,3,3-pentafluoropropyl group, a 2,2,2-trifluoro-1-trifluoromethylethyl group, a 1,1-bis(trifluoromethyl)-2,2,2-trifluoroethyl group, a 2-fluorophenyl group, a 3-fluorophenyl group, a 4-fluorophenyl group, a

2,4-difluorophenyl group, a 2,6-difluorophenyl group, a
 3,4-difluorophenyl group, a 3,5-difluorophenyl group, a
 2,4,6-trifluorophenyl group, a 3,4,5-trifluorophenyl group,
 a 2,3,5,6-tetrafluorophenyl group, a pentafluorophenyl group,
 5 a 2,3,5,6-tetrafluoro-4-trifluoromethylphenyl group, a
 2,3,5,6-tetrafluoro-4-pentafluorophenylphenyl group, a
 perfluoro-1-naphthyl group, a perfluoro-2-naphthyl group, a
 chloromethyl group, a dichloromethyl group, a trichloromethyl
 group, a 2,2,2-trichloroethyl group, a
 10 2,2,3,3,3-pentachloropropyl group, a
 2,2,2-trichloro-1-trichloromethylethyl group, a
 1,1-bis(trichloromethyl)-2,2,2-trichloroethyl group, a
 4-chlorophenyl group, a 2,6-dichlorophenyl group, a
 3,5-dichlorophenyl group, a 2,4,6-trichlorophenyl group or a
 15 pentachlorophenyl group. Particularly preferred is a
 fluoroalkyl group or a fluoroaryl group, and the most preferred
 is a trifluoromethyl group,
 2,2,2-trifluoro-1-trifluoromethylethyl group,
 1,1-bis(trifluoromethyl)-2,2,2-trifluoroethyl group,
 20 3,5-difluorophenyl group or 3,4,5-trifluorophenyl group,
 pentafluorophenyl group.

Specific examples of the compound (a) include halogenated
 bismuths such as bismuth(III)fluoride, bismuth(III)chloride,
 bismuth(III)bromide and bismuth(III)iodide; trialkyl bismuths
 25 such as trimethyl bismuth; triaryl bismuths such as triphenyl
 bismuth; trialkoxy bismuths such as trimethoxy bismuth and
 triethoxy bismuth; triaryl bisbuths such as triphenoxy bismuth;
 halogenated bismuths(V) such as bismuth(V)fluoride,
 bismuth(V)chloride, bismuth(V)bromide and bismuth(V)iodide;

pentaalkyl bismuths such as pentamethyl bismuth; pentaalkoxy bismuths such as pentamethoxy bismuth and pentaethoxy bismuth; and pentaaryloxy bismuths such as pentaphenoxy bismuth.

The compound(a) preferably include halogenated
5 bismuths(III), trialkyl bismuths, triaryl bismuths, trialkoxy bismuths, triaryloxy bismuths, more preferred is halogenated bismuths(III), triaryl bismuths, trialkoxy bismuths or triaryloxy bismuths, and particularly preferred are triaryl bismuths such as triphenyl bismuth.

10 Specific examples of the compounds (b) include amines such as di(fluoromethyl)amine, di(chloromethyl)amine, di(bromomethyl)amine, di(iodomethyl)amine, bis(difluoromethyl)amine, bis(dichloromethyl)amine, bis(dibromomethyl)amine, bis(diiodomethyl)amine,
15 bis(trifluoromethyl)amine, bis(trichloromethyl)amine, bis(tribromomethyl)amine, bis(triiodomethyl)amine, bis(2,2,2-trifluoroethyl) amine, bis(2,2,2-trichloroethyl)amine, bis(2,2,2-tribromoethyl)amine, bis(2,2,2-triiodoethyl)amine,
20 bis(2,2,3,3,3-pentafluoropropyl)amine, bis(2,2,3,3,3-pentachloropropyl)amine, bis(2,2,3,3,3-pentabromopropyl)amine, bis(2,2,3,3,3-pentaiodopropyl)amine, bis(2,2,2-trifluoro-1-trifluoromethylethyl)amine, bis(2,2,2-trichloro-1-trichloromethylethyl)amine,
25 bis(2,2,2-tribromo-1-tribromomethylethyl)amine, bis(2,2,2-triiodo-1-triiodomethylethyl)amine, bis(1,1-bis(trifluoromethyl)-2,2,2-trifluoroethyl)amine, bis(1,1-bis(trichloromethyl)-2,2,2-trichloroethyl)amine, bis(1,1-bis(tribromomethyl)-2,2,2-tribromoethyl)amine,

bis(1,1-bis(triiodomethyl)-2,2,2-triiodoethyl)amine,
 bis(2-fluorophenyl)amine, bis(3-fluorophenyl)amine,
 bis(4-fluorophenyl)amine, bis(2-chlorophenyl)amine,
 bis(3-chlorophenyl)amine, bis(4-chlorophenyl)amine,
 5 bis(2-bromophenyl)amine, bis(3-bromophenyl)amine,
 bis(4-bromophenyl)amine, bis(2-iodophenyl)amine,
 bis(3-iodophenyl)amine, bis(4-iodophenyl)amine,
 bis(2,6-difluorophenyl)amine, bis(3,5-difluorophenyl)amine,
 bis(2,6-dichlorophenyl)amine, bis(3,5-dichlorophenyl)amine,
 10 bis(2,6-dibromophenyl)amine, bis(3,5-dibromophenyl)amine,
 bis(2,6-diiodophenyl)amine, bis(3,5-diiodophenyl)amine,
 bis(2,4,6-trifluorophenyl)amine,
 bis(2,4,6-trichlorophenyl)amine,
 bis(2,4,6-tribromophenyl)amine,
 15 bis(2,4,6-triiodophenyl)amine,
 bis(pentafluorophenyl)amine, bis(pentachlorophenyl)amine,
 bis(pentabromophenyl)amine, bis(pentaiodophenyl)amine,
 bis(2-(trifluoromethyl)phenyl)amine,
 bis(3-(trifluoromethyl)phenyl)amine,
 20 bis(4-(trifluoromethyl)phenyl)amine,
 bis(2,6-di(trifluoromethyl)phenyl)amine,
 bis(3,5-di(trifluoromethyl)phenyl)amine,
 bis(2,4,6-tri(trifluoromethyl)phenyl)amine,
 bis(2-cyanophenyl)amine, bis(3-cyanophenyl)amine,
 25 bis(4-cyanophenyl)amine, bis(2-nitrophenyl)amine,
 bis(3-nitrophenyl)amine, bis(4-nitrophenyl)amine, bis(1H,
 1H-perfluorobutyl)amine, bis(1H,1H-perfluorobutyl)amine,
 bis(1H,1H-perfluoropentyl)amine,
 bis(1H, 1H-perfluorohexyl)amine,

bis(1H, 1H-perfluorooctyl)amine,
 bis(1H, 1H-perfluorododecyl)amine,
 bis(1H, 1H-perfluoropentadecyl)amine,
 bis(1H, 1H-perfluoroeicocyl)amine, bis(1H,
 5 1H-perchlorobutyl)amine, bis(1H,1H-perchlorobutyl)amine,
 bis(1H,1H-perchloropentyl)amine,
 bis(1H, 1H-perchlorohexyl)amine,
 bis(1H, 1H-perchlorooctyl)amine,
 bis(1H, 1H-perchlorododecyl)amine,
 10 bis(1H, 1H-perchloropentadecyl)amine,
 bis(1H, 1H-perchloroeicocyl)amine, bis(1H,
 1H-perbromobutyl)amine, bis(1H,1H-perbromobutyl)amine,
 bis(1H,1H-perbromopentyl)amine,
 bis(1H, 1H-perbromohexyl)amine,
 15 bis(1H, 1H-perbromooctyl)amine,
 bis(1H, 1H-perbromododecyl)amine,
 bis(1H, 1H-perbromopentadecyl)amine,
 bis(1H, 1H-perbromoeicocyl)amine. Further, phosphine
 compounds in which a nitrogen atom is substituted by a
 20 phosphorous atom can be also exemplified similarly. Those
 phosphine compounds in which a nitrogen atom is replaced with
 a phosphorus atom in the above-mentioned amine compounds, and
 the like are also exemplified compounds which are represented
 by replacing amine in the above-mentioned specific examples
 25 by phosphine, etc.

Alcohols include fluoromethanol, chloromethanol,
 bromomethanol, iodomethanol, difluoromethanol,
 dichloromethanol, dibromomethanol, diiodomethanol,
 trifluoromethanol, trichloromethanol, tribromomethanol,

triiodomethanol, 2,2,2-trifluoroethanol,
 2,2,2-trichloroethanol, 2,2,2-tribromoethanol,
 2,2,2-triiodoethanol, 2,2,3,3,3-pentafluoropropanol,
 2,2,3,3,3-pentachloropropanol, 2,2,3,3,3-pentabromopropanol,
 5 2,2,3,3,3-pentaiodopropanol,
 2,2,2-trifluoro-1-trifluoromethylethanol,
 2,2,2-trichloro-1-trichloromethylethanol,
 2,2,2-tribromo-1-tribromomethylethanol,
 2,2,2-triiodo-1-triiodomethylethanol,
 10 1,1-bis(trifluoromethyl)-2,2,2-trifluoroethanol,
 1,1-bis(trichloromethyl)-2,2,2-trichloroethanol,
 1,1-bis(tribromomethyl)-2,2,2-tribromoethanol,
 1,1-bis(triiodomethyl)-2,2,2-triiodoethanol,
 1H,1H-perfluorobutanol, 1H,1H-perfluoropentanol,
 15 1H,1H-perfluorohexanol, 1H,1H-perfluorooctanol,
 1H,1H-perfluorododecanol, 1H,1H-perfluoropentadecanol,
 1H,1H-perfluoroeicosanol, 1H,1H-perchlorobutanol,
 1H,1H-perchloropentanol, 1H,1H-perchlorohexanol,
 1H,1H-perchlorooctanol, 1H,1H-perchlorododecanol,
 20 1H,1H-perchloropentadecanol, 1H,1H-perchloroeicosanol,
 1H,1H-perbromobutanol, 1H,1H-perbromopentanol,
 1H,1H-perbromohexanol, 1H,1H-perbromooctanol,
 1H,1H-perbromododecanol, 1H,1H-perbromopentadecanol and
 1H,1H-perbromoeicosanol. Further, thiol compounds in which an
 25 oxygen atom is replaced with substituted by a sulfur atom can
 be also exemplified similarly. Those thiol compounds are
 compounds which are represented by replacing methanol in the
 above-described specific example by methanethiol, ethanol by
 ethanethiol, propanol by propanethiol, butanol by butanethiol,

pentanol by pentanethiol, hexanol by hexanethiol, octanol by octanethiol, dodecanol by dodecanethiol, pentadecanol by pentadecanethiol and eicosanol by eicosanethiol.

The phenols include 2-fluorophenol, 3-fluorophenol,
5 4-fluorophenol, 2,4-difluorophenol, 2,6-difluorophenol,
3,4-difluorophenol, 3,5-difluorophenol,
2,4,6-trifluorophenol, 3,4,5-trifluorophenol,
2,3,5,6-tetrafluorophenol, pentafluorophenol,
2,3,5,6-tetrafluoro-4-trifluoromethylphenol,
10 2,3,5,6-tetrafluoro-4-pentafluorophenylphenol,
perfluoro-1-naphtol, perfluoro-2-naphtol, 2-chlorophenol,
3-chlorophenol, 4-chlorophenol, 2,4-dichlorophenol,
2,6-dichlorophenol, 3,4-dichlorophenol, 3,5-dichlorophenol,
2,4,6-trichlorophenol, 3,4,5-trichlorophenol,
15 2,3,5,6-tetrachlorophenol, pentachlorophenol,
2,3,5,6-tetrachloro-4-trichloromethylphenol,
2,3,5,6-tetrachloro-4-pentachlorophenylphenol,
perchloro-1-naphtol, perchloro-2-naphtol, 2-bromophenol,
3-bromophenol, 4-bromophenol, 2,4-dibromophenol,
20 2,6-dibromophenol, 3,4-dibromophenol, 3,5-dibromophenol,
2,4,6-tribromophenol, 3,4,5-tribromophenol,
2,3,5,6-tetrabromophenol, pentabromophenol,
2,3,5,6-tetrabromo-4-tribromomethylphenol,
2,3,5,6-tetrabromo-4-pentabromophenylphenol,
25 perbromo-1-naphtol, perbromo-2-naphtol, 2-iodophenol,
3-iodophenol, 4-iodophenol, 2,4-diiodophenol,
2,6-diiodophenol, 3,4-diiodophenol, 3,5-diiodophenol,
2,4,6-triiodophenol, 3,4,5-triiodophenol,
2,3,5,6-tetraiodophenol, pentaiodophenol,

2,3,5,6-tetraiodo-4-triiodomethylphenol,
2,3,5,6-tetraiodo-4-pentaiodophenylphenol,
periodo-1-naphtol, periodo-2-naphtol,
2-(trifluoromethyl)phenol, 3-(trifluoromethyl)phenol,
5 4-(trifluoromethyl)phenol, 2,6-bis(trifluoromethyl) phenol,
3,5-bis(trifluoromethyl)phenol,
2,4,6-tris(trifluoromethyl)phenol, 2-cyanophenol,
3-cyanophenol, 4-cyanophenol, 2-nitrophenol, 3-nitrophenol,
4-nitrophenol and the like. Further, thiophenol compounds in
10 which an oxygen atom is substituted by a sulfur atom in the
above-mentioned phenol compounds can be also exemplified
similarly. Those thiophenol compounds are compounds which are
represented by replacing phenol in the above-mentioned specific
examples by thiophenol (in a case of naphtols, compounds
15 represented by replacing naphtols with naphtylthiols).

Carboxylic acids include pentafluorobenzoic acid,
perfluoroethanoic acid, perfluoropropanoic acid,
perfluorobutanoic acid, perfluoropentanoic acid,
perfluorohexanoic acid, perfluoroheptanoic acid,
20 perfluorooctanoic acid, perfluorononanoic acid,
perfluorodecanoic acid, perfluoroundecanoic acid,
perfluorododecanoic acid and the like.

Preferable compounds (b) are bis(trifluoromethyl)amine,
bis(2,2,2-trifluoromethyl)amine,
25 bis(2,2,3,3,3-pentafluoropropyl)amine,
bis(2,2,2-trifluoro-1-trifluoromethylethyl)amine,
bis(1,1-bis(trifluoromethyl)-2,2,2-trifluoroethyl)amine or
bis(pentafluorophenyl)amine as amines; trifluoromethanol,
2,2,2-trifluoroethanol, 2,2,3,3,3-pentafluoropropanol,

2,2,2-trifluoro-1-trifluoromethylethanol or
1,1-bis(trifluoromethyl)-2,2,2-trifluoroethanol as
alcohols; and 2-fluorophenol, 3-fluorophenol, 4-fluorophenol,
2,6-difluorophenol, 3,5-difluorophenol,
5 3,4,5-trifluorophenol, 2,4,6-trifluorophenol,
pentafluorophenol, 2-(trifluoromethyl)phenol,
3-(trifluoromethyl)phenol, 4-(trifluoromethyl)phenol,
2,6-bis(trifluoromethyl)phenol,
3,5-bis(trifluoromethyl)phenol or
10 2,4,6-tris(trifluoromethyl)phenol as phenols.

The compounds (b) are more preferably,
bis(trifluoromethyl)amine, bis(pentafluorophenyl) amine,
trifluoromethanol, 2,2,2-trifluoro-1-trifluoromethylethanol,
1,1-bis(trifluoromethyl)-2,2,2-trifluoroethanol,
15 2-fluorophenol, 3-fluorophenol, 4-fluorophenol,
2,6-difluorophenol, 3,5-difluorophenol,
2,4,6-trifluorophenol, 3,4,5-trifluorophenol,
pentafluorophenol, 4-(trifluoromethyl)phenol,
2,6-bis(trifluoromethyl)phenol or
20 2,4,6-tris(trifluoromethyl)phenol, and further preferably
3,5-difluorophenol, 3,4,5-trifluorophenol,
pentafluorophenol or
1,1-bis(trifluoromethyl)-2,2,2-trifluoroethanol.

As the particle (c), that which is generally used as a
25 carrier is preferably used. A porous substance having a
uniform particle diameter is preferred and an inorganic
substance or an organic polymer is preferably used. An inorganic
substance is more preferably used.

From a viewpoint of particle size distribution of a polymer

obtained, the particle (c) has a geometric standard deviation of preferably not more than 2.5, more preferably not more than 2.0, and much more preferably not more than 1.7, wherein the geometric standard deviation is based on a volume of a particle
5 diameter of the particle (c).

Examples of the inorganic substance used as the particle (c) are inorganic oxides. It is also permitted to use clay and clay mineral. These inorganic substances may be used in a mixture.

10 Specific examples of the inorganic oxide include SiO_2 , Al_2O_3 , MgO , ZrO_2 , TiO_2 , B_2O_3 , CaO , ZnO , BaO , ThO_2 and mixtures thereof such as $\text{SiO}_2\text{-MgO}$, $\text{SiO}_2\text{-Al}_2\text{O}_3$, $\text{SiO}_2\text{-TiO}_2$, $\text{SiO}_2\text{-V}_2\text{O}_5$, $\text{SiO}_2\text{-Cr}_2\text{O}_3$ and $\text{SiO}_2\text{-TiO}_2\text{-MgO}$. Among these inorganic oxides, SiO_2 and/or Al_2O_3 are/is preferred, and SiO_2 is particularly preferred.
15 Incidentally, the above inorganic oxide may contain a small amount of carbonates, sulfates, nitrates and oxide components, such as Na_2CO_3 , K_2CO_3 , CaCO_3 , MgCO_3 , Na_2SO_4 , $\text{Al}_2(\text{SO}_4)_3$, BaSO_4 , KNO_3 , $\text{Mg}(\text{NO}_3)_2$, $\text{Al}(\text{NO}_3)_3$, Na_2O , K_2O and Li_2O .

Examples of the clay or clay mineral are kaolin, bentonite,
20 Kibushi clay, gaerome clay, allophane, hisingerite, pyrophyllite, talc, a mica group, a montmorillonite group, vermiculite, a chlorite group, palygorskite, kaolinite, nacrite, dickite and halloysite. Among these, smectite, montmorillonite, hectorite, raponite and saponite are
25 preferred, and montmorillonite and hectorite are more preferred.

Among these inorganic substances, inorganic oxides are suitably used.

It is preferable that these inorganic substances are dried

to contain substantially no water, and those dried by heat-treatment are preferred. The heat-treatment of inorganic substances, whose water content cannot be visually confirmed, is usually carried out at a temperature of from 100 to 1500°C, preferably from 100 to 1000°C, and more preferably from 200 to 800°C. The heating time is not particularly limited, and preferably from 10 minutes to 50 hours, more preferably from 1 hour to 30 hours. Further, during heating, there can be applied a method of passing a dried inert gas (e.g. nitrogen or argon) at a fixed flow rate, or a method of evacuating. The method is not limited thereto.

Further, though hydroxy groups are formed and exist on the surface of the inorganic oxides, modified inorganic oxides obtained by substituting active hydrogen of hydroxy groups on the surface of the inorganic oxides with various substituents, may be used as the inorganic oxides. As a substituted group, a silyl group is preferred. As the modified inorganic oxides, specifically there are illustrated inorganic oxides obtained by contact-treating with a trialkylchlorosilane such as trimethylchlorosilane, t-butyldimethylchlorosilane, dichlorodimethylsilane or chlorobromodimethylsilane; a triarylchlorosilane such as triphenylchlorosilane; a dialkyldichlorosilane such as dimethyldichlorosilane; a diaryldichlorosilane such as diphenyldichlorosilane; an alkyltrichlorosilane such as methyltrichlorosilane; an aryltrichlorosilane such as phenyltrichlorosilane; a trialkylalkoxysilane such as trimethylmethoxysilane; a triarylalkoxysilane such as triphenylmethoxysilane; a dialkyldialkoxysilane such as dimethyldimethoxysilane; a

diaryldialkoxysilane such as diphenyldimethoxysilane; an alkyltrialkoxysilane such as methyltrimethoxysilane; an aryltrialkoxysilane such as phenyltrimethoxysilane; a tetraalkoxysilane such as tetramethoxysilane; an alkyl
5 disilazane such as 1,1,1,3,3,3-hexamethyldisilazane; or tetrachlorosilane.

A median particle diameter of the inorganic substance is preferably from 5 to 1000 μm , more preferably from 10 to 500 μm , and more preferably from 10 to 100 μm . A pore volume
10 is preferably not less than 0.1 ml/g, and more preferably 0.3 to 10ml/g. The specific surface area is preferably from 10 to 1000 m^2/g , and more preferably from 100 to 500 m^2/g .

The organic polymer usable as the particle (c) may be any organic polymer, and it is permitted to use a mixture of
15 more than one organic polymer. As the organic polymer, a polymer having an active hydrogen-carrying functional group or a functional group of a non-proton-donating Lewis base is preferred.

The active hydrogen-carrying functional group is not
20 particularly limited as far as it has active hydrogen. Examples thereof are a primary amino group, a secondary amino group, an imino group, an amide group, a hydrazide group, an amidino group, a hydroxy group, a hydroperoxy group, a carboxyl group, a formyl group, a carbamoyl group, a sulfonic acid group, a
25 sulfinic acid group, a sulfenic acid group, a thiol group, a thioformyl group, a pyrrolyl group, an imidazolyl group, a piperidyl group, an indazolyl group and a carbazolyl group. Among them, preferred is a primary amino group, a secondary amino group, an imino group, an amide group, an imide group,

a hydroxy group, a formyl group, a carboxyl group, a sulfonic acid group or a thiol group. Particularly preferred is a primary amino group, a secondary amino group, an amide group or a hydroxy group. These groups may be substituted with a halogen atom
5 or a hydrocarbon group having 1 to 20 carbon atoms.

The functional group of a non-proton-donating Lewis base is not particularly limited as far as it is a functional group having a Lewis base portion containing no active hydrogen atom. Specific examples thereof are a pyridyl group, an N-substituted
10 imidazolyl group, an N-substituted indazolyl group, a nitrile group, an azido group, an N-substituted imino group, an N,N-substituted aminogroup, an N,N-substituted aminoxy group, an N,N,N-substituted hydrazino group, a nitroso group, a nitro group, a nitroxy group, a furyl group, a carbonyl group, a
15 thiocarbonyl group, an alkoxy group, an alkyloxycarbonyl group, an N,N-substituted carbamoyl group, a thioalkoxy group, a substituted sulfinyl group, a substituted sulfonyl group and a substituted sulfonic acid group. Preferred is a heterocyclic group, and more preferred is an aromatic heterocyclic group
20 having an oxygen atom and/or a nitrogen atom in the ring. Particularly preferred are a pyridyl group, an N-substituted imidazolyl group and an N-substituted indazolyl group, and the most preferred is a pyridyl group. These groups may be substituted with a halogen atom or a hydrocarbon group having
25 1 to 20 carbon atoms.

An amount of the active hydrogen-carrying functional group or the functional group of a non-proton-donating Lewis base is not particularly limited. It is preferably from 0.01 to 50 mmol/g, and more preferably from 0.1 to 20 mmol/g, in

terms of a molar amount of the functional group per g of the organic polymer.

The functional group-carrying organic polymer can be obtained, for example, by homopolymerizing a monomer having the active hydrogen-carrying functional group or the functional group of a non-proton-donating Lewis base and more than one polymerizable unsaturated group, or copolymerizing said monomer and another monomer having a polymerizable unsaturated group. At this time, it is preferred to additionally copolymerize a crosslinking polymerizable monomer having two or more polymerizable unsaturated groups.

Examples of the monomer having the active hydrogen-carrying functional group or the functional group of a non-proton-donating Lewis base and more than one polymerizable unsaturated group are monomers having the above-mentioned active hydrogen-carrying functional group and more than one polymerizable unsaturated group, and monomers having the above-mentioned functional group having a Lewis base portion containing no active hydrogen and more than one polymerizable unsaturated group. Examples of the polymerizable unsaturated group are an alkenyl groups such as a vinyl group and an allyl group, and an alkynyl group such as an ethyne group.

Examples of the monomer having the active hydrogen-carrying functional group and more than one polymerizable unsaturated group are a vinyl group-containing primary amine, a vinyl group-containing secondary amine, a vinyl group-containing amide compound and a vinyl group-containing hydroxy compound. Specific examples thereof are

N-(1-ethenyl)amine, N-(2-propenyl)amine,
N-(1-ethenyl)-N-methylamine, N-(2-propenyl)-N-methylamine,
1-ethenylamide, 2-propenylamide, N-methyl-(1-ethenyl)amide,
N-methyl-(2-propenyl)amide, vinyl alcohol and 2-propen-1-ol
5 and 3-buten-1-ol.

Specific examples of the monomer having the functional
group having a Lewis base portion containing no active hydrogen
and more than one polymerizable unsaturated group are
vinylpyridine, vinyl(N-substituted)imidazole and
10 vinyl(N-substituted)indazole.

The other monomers having a polymerizable unsaturated
group include ethylene, α -olefins and aromatic vinyl compounds,
and specific examples thereof are ethylene, propylene, 1-butene,
1-hexene, 4-methyl-1-pentene and styrene. Preferred is
15 ethylene or styrene. These monomers may be used in a combination
of two or more.

As specific examples of the crosslinking polymerizable
monomer having two or more polymerizable unsaturated groups,
divinylbenzene can be given.

20 A median particle diameter of the organic polymer is
preferably from 5 to 1000 μm , and more preferably from 10 to
500 μm . A pore volume is preferably not less than 0.1 ml/g,
and more preferably 0.3 to 10 ml/g. A specific surface area
is preferably from 10 to 1000 m^2/g , and more preferably from
25 50 to 500 m^2/g .

It is preferable that these organic polymers are dried
to contain substantially no water, and those dried by
heat-treatment are preferred. The heat-treatment of organic
polymers, whose water content cannot be visually confirmed,

is usually carried out at a temperature of from 30 to 400°C, preferably from 50 to 200°C, and more preferably from 70 to 150°C. The heating time is not particularly limited, and preferably from 30 minutes to 50 hours, more preferably from 1 hour to 30 hours. Further, during heating, there can be used a method of passing a dried inert gas (e.g. nitrogen or argon) at a fixed flow rate, or a method of evacuating. The method is not limited thereto.

The modified particle in accordance with the present invention is a modified particle obtained by contacting the above-mentioned (a), (b) and (c) with one another. An order for contacting (a), (b) and (c) is not particularly limited, and the following orders are enumerated.

<1> A contact product obtained by contacting a contact product between (a) and (b) with (c).

<2> A contact product obtained by contacting a contact product between (a) and (c) with (b).

<3> A contact product obtained by contacting a contact product between (b) and (c) with (a).

A preferable contact order is the above-mentioned <1> or <2>, and the most preferable is <1>.

It is preferable to carry out the contact treatment under an inert gas atmosphere. A treating temperature is usually from -100 to 300°C, and preferably from -80 to 200°C. A treating time is usually from 1 minute to 200 hours, and preferably from 10 minutes to 100 hours. It is permitted to carry out such a treatment using a solvent or directly treat the compounds without use of any solvent.

Examples of solvents usable are non-polar solvents such

as aliphatic hydrocarbon solvents and aromatic hydrocarbon solvents; and polar solvents such as halogenide solvents and ether solvents. Specific examples thereof include aliphatic hydrocarbon solvents such as butane, pentane, hexane, heptane, 5 octane, 2,2,4-trimethylpentane and cyclohexane; aromatic hydrocarbon solvents such as benzene, toluene and xylene; halogenide solvents such as dichloromethane, difluoromethane, chloroform, 1,2-dichloroethane, 1,2-dibromoethane, 1,1,2-trichloro-1,2,2-trifluoroethane, tetrachloroethylene, 10 chlorobenzene, bromobenzene and o-dichlorobenzene; ether solvents such as dimethyl ether, diethyl ether, diisopropyl ether, di-n-butyl ether, methyl-tert-butyl ether, anisole, 1,4-dioxane, 1,2-dimethoxyethane, bis(2-methoxyethyl) ether, tetrahydrofuran and tetrahydropyran.

15 An amount used of the compound (b) to the compound(a) is not particularly limited. However, it is preferred that a molar ration substantially satisfies a number of 0.1 to 8.

 The number is more preferably 1 to 6, further preferably 2 to 4, and most preferably 2.5 to 3.5.

20 In preparation of the modified particle in accordance with the present invention, it is permitted to appropriately determine a proportion of (c) to (a), provided that a bismuth atom originated from (a) and contained in a particle obtained by contacting (a) and (c) with each other is controlled so as 25 to be preferably not less than 0.1 mmol, and more preferably from 0.5 to 20 mmol, in terms of a mol number of a bismuth atom contained in 1 g of the obtained particle.

 As a result of such a contact treatment, at least one of the starting (a), (b) and/or (c) may remain as an unreacted

material in the modified particle of the present invention. But, when it is applied to polymerization accompanying formation of addition polymer particles, it is preferable to conduct washing for previously removing the unreacted material. A solvent used therefor may be the same or different from the solvent used at the time of contact. Such the washing is preferably carried out under atmosphere of an inert gas. A treating temperature is usually -100 to 300°C, preferably -80 to 200°C. A treating time is usually 1 minute to 200 hours, preferably 10 minutes to 100 hours.

Further, after completion of such the contact treatment and washing, preferably, the solvent is removed from the product by distillation, and the resulting product is dried under reduced pressure at a temperature of not lower than 25°C for 1 to 24 hours, more preferably at a temperature of from 40 to 200°C for 1 to 24 hours, much more preferably at a temperature of from 60 to 200°C for 1 to 24 hours, particularly preferably at a temperature of from 60 to 160°C for 2 to 18 hours and the most preferably at a temperature of from 80 to 160°C for 4 to 18 hours.

A specific example of a process for producing the modified particle in accordance with the present invention is explained in more detail as follows, wherein the compound(a) is triphenyl bismuth, the compound(b) is pentafluorophenol, and the particle (c) is silica. Toluene is used as a solvent, triphenyl bismuth is added thereto, a toluene solution of pentafluorophenol of 3 mol to 1 mol of bismuth is added dropwise thereto, and then stirring is carried out under refluxing for 10 minutes to 24 hours after stirring at room temperature for 10 minutes to 24

hours. Thereafter, the solution is concentrated, and a precipitated solid component is filtered and dried.

To a solid component obtained through the above-mentioned operations, toluene and silica are added, and the mixture is stirred at 80°C for 2 hours. The resulting solid component is washed with toluene, and dried under reduced pressure.

The modified particle of the present invention can be thus produced.

The modified particle in accordance with the present invention is useful as a catalyst component for addition polymerization (particularly, the catalyst component for olefin polymerization) As the catalyst for addition polymerization in accordance with the present invention, there are exemplified a catalyst for addition polymerization obtained by contacting the above-mentioned modified particle (A) of the present invention obtained by contacting the above (a) with (b), with a metal compound (B) of the Groups 3 to 11 or lanthanoide series, and a catalyst for addition polymerization obtained by contacting the above-mentioned modified particle (A) of the present invention, a transition metal compound (B) of the Groups 3 to 11 or lanthanoide series and an organoaluminum compound (C). The latter is higher in activity and more preferred.

The catalyst for addition polymerization is explained below in more detail.

(B) Transition metal compound of the Groups 3 to 11 or Lanthanoide Series

As the transition metal compound (B) of the Groups 3 to 11 or lanthanoide series used for the catalyst for addition polymerization in accordance with the present invention, a

transition metal compound capable of forming a single site catalyst is used. It is not particularly limited as far as it is a transition metal compound of the Groups 3 to 11 or lanthanoid series, and exhibits addition polymerization activity when used in combination with the above-mentioned modified particle (A) (and additionally organoaluminum compound (C)) as a co-catalyst component for activation use.

Besides, herein, "single-site catalyst" is a conception distinctable from "conventional solid catalyst" and includes not only a single-site catalyst in a narrow sense, which can obtain a addition polymer having a narrow molecular weight distribution and narrow composition distribution in a copolymer, but also a catalyst which can obtain an addition polymer having a wide molecular weight distribution and a wide composition distribution in a copolymer if the catalyst is obtained by a method similar to the preparation method of such a single-site catalyst in a narrow sense.

As such a transition metal compound (B), preferred is a transition metal compound represented by the following formula [3] or its μ -oxo type transition metal compound dimer.



(wherein M is a transition metal atom of the Groups 3 to 11 or lanthanoid series, L^2 is a cyclopentadienyl type anion skeleton-carrying group or a hetero atom-containing group, more than one L^2 may be linked directly or through a residual group containing a carbon atom, a silicone atom, a nitrogen atom, an oxygen atom, a sulfur atom or a phosphorus atom, X^1 is a halogen atom or a hydrocarbon group (provided that a cyclopentadienyl type anion skeleton-carrying group is

excluded) or OR (R represents a hydro carbon group or halogenated hydro carbon group, and when more than one R, they may be the same or different each other), a is a number satisfying $0 < a \leq 8$, and b is a number satisfying $0 < b \leq 8$.)

5 In the formula [3], M is a transition metal atom of the Groups 3 to 11 of the periodic table (IUPAC 1989) or lanthanoid series. Examples thereof are a scandium atom, an yttrium atom, a titanium atom, a zirconium atom, a hafnium atom, a vanadium atom, a niobium atom, a tantalum atom, a chromium atom, an iron atom, a ruthenium atom, a cobalt atom, a rhodium atom, a nickel atom, a palladium atom, a samarium atom and an ytterbium atom. Preferred as M in the formula [3] is a titanium atom, a zirconium atom, a hafnium atom, a vanadium atom, a chromium atom, an iron atom, a cobalt atom or a nickel atom, and particularly preferred
10 is a titanium atom, a zirconium atom or a hafnium atom.
15

In the formula [3], L^2 is a cyclopentadienyl type anion skeleton-carrying group or a hetero atom-containing group, and more than one L^2 may be the same or different from one another. Further, more than one L^2 may be linked directly or through
20 a residual group containing a carbon atom, a silicone atom, a nitrogen atom, an oxygen atom, a sulfur atom or a phosphorus atom.

Examples of the cyclopentadienyl type anion skeleton-carrying group as L^2 are η^5 -(substituted) cyclopentadienyl groups, η^5 -(substituted)indenyl groups and η^5 -(substituted) fluorenyl groups. Specific examples thereof are an η^5 -cyclopentadienyl group, an η^5 -methylcyclopentadienyl group, an η^5 -ethylcyclopentadienyl group, an η^5 -n-butylcyclopentadienyl group, an η^5 -

- 5-tert-butylcyclopentadienyl group, an η
- 5-1,2-dimethylcyclopentadienyl group, an η
- 5-1,3-dimethylcyclopentadienyl group, an η
- 5-1-methyl-2-ethylcyclopentadienyl group, an η
- 5 5-1-methyl-3-ethylcyclopentadienyl group, an η
- 5-1-tert-butyl-2-methylcyclopentadienyl group, an η
- 5-1-tert-butyl-3-methylcyclopentadienyl group, an η
- 5-1-methyl-2-isopropylcyclopentadienyl group, an η
- 5-1-methyl-3-isopropylcyclopentadienyl group, an η
- 10 5-1-methyl-2-n-butylcyclopentadienyl group, an η
- 5-1-methyl-3-n-butylcyclopentadienyl group,
an η 5-1,2,3-trimethylcyclopentadienyl group, an η
- 5-1,2,4-trimethylcyclopentadienyl group, an η
- 5-tetramethylcyclopentadienyl group, an η
- 15 5-pentamethylcyclopentadienyl group, an η 5-indenyl group, an
 η 5-4,5,6,7-tetrahydroindenyl group, an η 5-2-methylindenyl
group, an η 5-3-methylindenyl group, an η 5-4-methylindenyl
group, an η 5-5-methylindenyl group, an η 5-6-methylindenyl
group, an η 5-7-methylindenyl group, an η 5-2-tert-butylindenyl
20 group, an η 5-3-tert-butylindenyl group, an η
- 5-4-tert-butylindenyl group, an η 5-5-tert-butylindenyl group,
an η 5-6-tert-butylindenyl group, an η 5-7-tert-butylindenyl
group, an η 5-2,3-dimethylindenyl group, an η
- 5-4,7-dimethylindenyl group, an η 5-2,4,7-trimethylindenyl
25 group, an η 5-2-methyl-4-isopropylindenyl group, an η
- 5-4,5-benzindenyl group, an η 5-2-methyl-4,5-benzindenyl group,
an η 5-4-phenylindenyl group, an η 5-2-methyl-5-phenylindenyl
group, an η 5-2-methyl-4-phenylindenyl group, an η
- 5-2-methyl-4-naphthylindenyl group, an η 5-fluorenyl group, an

η^5 -2,7-dimethylfluorenyl group, an η^5 -2,7-di-tert-butylfluorenyl group and their substitution compounds.


Incidentally, in the present specification, " η^5 -" in the name of the transition metal compound may be omitted in some cases.

The hetero atom in the above hetero atom-containing group includes an oxygen atom, a sulfur atom, a nitrogen atom and a phosphorus atom. Examples of such a group are preferably an alkoxy group, an aryloxy group, a thioalkoxy group, a thioaryloxy group, an alkylamino group, an arylamino group, an alkylphosphino group, an arylphosphino group, a chelating ligand, and an aromatic or aliphatic heterocyclic group having an oxygen atom, a sulfur atom, a nitrogen atom and/or a phosphorus atom in the ring.

Specific examples of the hetero atom-containing group are a methoxy group, an ethoxy group, a propoxy group, a butoxy group, a phenoxy group, a 2-methylphenoxy group, a 2,6-dimethylphenoxy group, a 2,4,6-trimethylphenoxy group, a 2-ethylphenoxy group, a 4-n-propylphenoxy group, a 2-isopropylphenoxy group, a 2,6-diisopropylphenoxy group, a 4-sec-butylphenoxy group, a 4-tert-butylphenoxy group, a 2,6-di-sec-butylphenoxy group, a 2-tert-butyl-4-methylphenoxy group, a 2,6-di-tert-butylphenoxy group, a 4-methoxyphenoxy group, a 2,6-dimethoxyphenoxy group, a 3,5-dimethoxyphenoxy group, a 2-chlorophenoxy group, a 4-nitrosophenoxy group, a 4-nitrophenoxy group, a 2-aminophenoxy group, a 3-aminophenoxy group, a 4-aminothiophenoxy group, a 2,3,6-trichlorophenoxy

group, a 2,4,6-trifluorophenoxy group, a thiomethoxy group, a dimethylamino group, a diethylamino group, a dipropylamino group, a diphenylamino group, an isopropylamino group, a tert-butylamino group, a pyrrolyl group, a dimethylphosphino group, a 2-(2-oxy-1-propyl)phenoxy group, a catecholato group, a 2-hydroxyphenoxy group, a resorcinolate group, a 3-hydroxyphenoxy group, a 4-isopropylcatecolate group, a 4-isopropyl-2-hydroxyphenoxy group, a 3-methoxycatecolate group, a 3-methoxy-2-hydroxyphenoxy group, a 1,8-dihydroxynaphthyl group, a 1,2-dihydroxynaphthyl group, a 2,2'-biphenyldiol group, a 1,1'-bi-2-naphthol group, a 2,2'-dihydroxy-6,6'-dimethylbiphenyl group, a 4,4',6,6'-tetra-tert-butyl-2,2'-methylenediphenoxy group and a 4,4',6,6'-tetramethyl-2,2'-isobutylidenediphenoxy group.

Further, as the above-mentioned hetero atom-containing group, there is exemplified a group represented by the following formula [4].




(In the formula, respective R^2 's are independently of one another a hydrogen atom, a halogen atom or a hydrocarbon group, and may be the same or different from one another, and two or more thereof may be bound with one another and may form a ring.)

Specific examples of R^2 in the above formula [4] are a hydrogen atom, a fluorine atom, a chlorine atom, a bromine atom, an iodine atom, a methyl group, an ethyl group, a n-propyl group, an isopropyl group, a n-butyl group, a tert-butyl group, a cyclopropyl group, a cyclobutyl group, a cycloheptyl group, a cyclohexyl group, a phenyl group, a 1-naphthyl group, a

2-naphthyl group and a benzyl group, but are not limited thereto.

Furthermore, as the hetero atom-containing group, there is also exemplified a group represented by the following formula [5].



5

(In the formula, respective R^3 's are independently of one another a hydrogen atom, a halogen atom, a hydrocarbon group, a halogenated hydrocarbon group, a hydrocarbyloxy group, a silyl group or an amino group, and may be the same or different from one another, and two or more thereof may be bound with one another and may form a ring.)

Specific examples of R^3 in the formula [5] are a hydrogen atom, a fluorine atom, a chlorine atom, a bromine atom, an iodine atom, a phenyl group, a 1-naphthyl group, a 2-naphthyl group, a tert-butyl group, a 2,6-dimethylphenyl group, a 2-fluorenyl group, a 2-methylphenyl group, a 4-trifluoromethylphenyl group, a 4-methoxyphenyl group, a 4-pyridyl group, a cyclohexyl group, a 2-isopropylphenyl group, a benzyl group, a methyl group, a triethylsilyl group, a diphenylmethylsilyl group, a 1-methyl-1-phenylethyl group, a 1,1-dimethylpropyl group and a 2-chlorophenyl group, but are not limited thereto.

20

The above-mentioned chelating ligand means a ligand having more than one coordinating position. Specific examples thereof are acetylacetonate, diimine, oxazoline, bisoxazoline,

terpyridine, acylhydrazone, diethylenetriamine,
triethylenetetramine, porphyrin, crown ether and cryptate.

Specific examples of the above-mentioned heterocyclic group are a pyridyl group, an N-substituted imidazolyl group
5 and an N-substituted indazolyl group. Preferable is a pyridyl group.

Two cyclopentadienyl type anion skeleton-carrying groups, the cyclopentadienyl type anion skeleton-carrying group and the hetero atom-containing group, or two hetero atom-containing
10 groups may be bound to each other directly or through a residual group containing at least one selected from the group consisting of a carbon atom, a silicone atom, a nitrogen atom, an oxygen atom, a sulfur atom and a phosphorus atom, respectively. As such a residual group, preferred is a divalent residual group
15 in which an atom binding two L^2 s is a carbon atom, a silicone atom, a nitrogen atom, an oxygen atom, a sulfur atom and/or a phosphorus atom. More preferred is a divalent residual group in which an atom binding two L^2 s is a carbon atom, a silicone atom, a nitrogen atom, an oxygen atom, a sulfur atom and/or
20 a phosphorus atom, provided that a minimum atom number of the atom binding two L^2 s is not more than 3 (a case where the atom binding two L^2 s is single is included). Specific examples thereof are alkylene groups such as a methylene group, an ethylene group and a propylene group; substituted alkylene groups such as a
25 dimethylmethylene group (an isoprolidene group) and a diphenylmethylene group, a silylene group; a substituted silylene group such as a dimethylsilylene group, a diethylsilylene group, a diphenylsilylene group and a tetramethyldisilylene group, dimethoxysililene group ; and a

hetero atom such as a nitrogen atom, an oxygen atom, a sulfur atom and a phosphorus atom. Particularly preferred are a methylene group, an ethylene group, a dimethylmethylene group (an isopropylidene group), a diphenylmethylene group, a dimethylsilylene group, a diethylsilylene group, a diphenylsilylene group and a dimethoxysilylene group.

In the formula [3], X^1 is a halogen atom or a hydrocarbon group or a OR. Specific examples of the halogen atom are a fluorine atom, a chlorine atom, a bromine atom and an iodine atom. Examples of the hydrocarbon group stated here are a methyl group, an ethyl group, a n-propyl group, an isopropyl group, a n-butyl group, a phenyl group and a benzyl group. Preferable X^1 is a halogen atom, an alkyl group having 1 to 20 carbon atoms, an aralkyl group having 7 to 20 carbon atoms, an aryl group having 6 to 20 carbon atoms or an alkenyl group having 3 to 20 carbon atoms.

Examples of the alkyl group having 1 to 20 carbon atoms include a methyl group, ethyl group, n-propyl group, isopropyl group, n-butyl group, sec-butyl group, tert-butyl group, isobutyl group, n-pentyl group, neopentyl group, isoamyl group, n-hexyl group, n-octyl group, n-decyl group, n-dodecyl group, n-pentadecyl group, n-eicosyl group and the like, and a methyl group, ethyl group, isopropyl group, tert-butyl group, isobutyl group or isoamyl group is more preferable.

All of these alkyl groups may be substituted with a halogen atom such as a fluorine atom, a chlorine atom, a bromine atom or an iodine atom. Examples of the alkyl group having 1 to 10 carbon atoms which is substituted with the halogen atom, include a fluoromethyl group, a trifluoromethyl group, a

chloromethyl group, a trichloromethyl group, a fluoroethyl group, a pentafluoroethyl group, a perfluoropropyl group, a perfluorobutyl group, a perfluorohexyl group, a perfluorooctyl group, a perchloropropyl group, a perchlorobutyl group, a
5 perbromopropyl group and the like.

Further, all of these alkyl groups may be partially substituted with an alkoxy group such as a methoxy group, an ethoxy group or the like, an aryloxy group such as a phenoxy group or the like or an aralkyloxy group such as a benzyloxy
10 group or the like, etc.

Examples of the aralkyl group having 7 to 20 carbon atoms include a benzyl group, a (2-methylphenyl)methyl group, a (3-methylphenyl)methyl group, a (4-methylphenyl)methyl group, a (2,3-dimethylphenyl)methyl group, a
15 (2,4-dimethylphenyl)methyl group, a (2,5-dimethylphenyl)methyl group, a (2,6-dimethylphenyl)methyl group, a (3,4-dimethylphenyl)methyl group, a (3,5-dimethylphenyl)methyl group, a
20 (2,3,4-trimethylphenyl)methyl group, a (2,3,5-trimethylphenyl)methyl group, a (2,3,6-trimethylphenyl)methyl group, a (3,4,5-trimethylphenyl)methyl group, a (2,4,6-trimethylphenyl)methyl group, a
25 (2,3,4,5-tetramethylphenyl)methyl group, a (2,3,4,6-tetramethylphenyl)methyl group, a (2,3,5,6-tetramethylphenyl)methyl group, a (pentamethylphenyl)methyl group, an (ethylphenyl)methyl group, a (n-propylphenyl)methyl group, an (isopropylphenyl)methyl

group, a (n-butylphenyl)methyl group, a (sec-butylphenyl)methyl group, a (tert-butylphenyl)methyl group, a (n-pentylphenyl)methyl group, a (neopentylphenyl)methyl group, a (n-hexylphenyl)methyl group, 5 a (n-octylphenyl)methyl group, a (n-decylphenyl)methyl group, a (n-dodecylphenyl)methyl group, a naphthylmethyl group, an anthracenylmethyl group and the like, and a benzyl group is more preferable.

All of these aralkyl groups may be partially substituted 10 with a halogen atom such as a fluorine atom, a chlorine atom, a bromine atom or an iodine atom, an alkoxy group such as a methoxy group, an ethoxy group or the like, an aryloxy group such as a phenoxy group or the like or an aralkyloxy group such as a benzyloxy group or the like, etc.

15 Examples of the aryl group having 6 to 20 carbon atoms include a phenyl group, a 2-tolyl group, a 3-tolyl group, a 4-tolyl group, a 2,3-xylyl group, a 2,4-xylyl group, a 2,5-xylyl group, a 2,6-xylyl group, a 3,4-xylyl group, a 3,5-xylyl group, a 2,3,4-trimethylphenyl group, a 2,3,5-trimethylphenyl group, 20 a 2,3,6-trimethylphenyl group, a 2,4,6-trimethylphenyl group, a 3,4,5-trimethylphenyl group, a 2,3,4,5-tetramethylphenyl group, a 2,3,4,6-tetramethylphenyl group, a 2,3,5,6-tetramethylphenyl group, a pentamethylphenyl group, an ethylphenyl group, a n-propylphenyl group, an 25 isopropylphenyl group, a n-butylphenyl group, a sec-butylphenyl group, a tert-butylphenyl group, a n-pentylphenyl group, a neopentylphenyl group, a n-hexylphenyl group, a n-octylphenyl group, a n-decylphenyl group, a n-dodecylphenyl group, a n-tetradecylphenyl group, a naphthyl

group, an anthracenyl group and the like, and a phenyl group is more preferable.

All of these aryl groups may be partially substituted with a halogen atom such as a fluorine atom, a chlorine atom, a bromine atom or, an iodine atom or the like, an alkoxy group such as a methoxy group, an ethoxy group or the like, an aryloxy group such as a phenoxy group or the like or an aralkyloxy group such as a benzyloxy group or the like, etc.

Examples of the alkenyl group having 3 to 20 carbon atoms include an allyl group, a methallyl group, a crotyl group, a 1,3-diphenyl-2-propenyl group and the like, and an allyl group and a methallyl group are more preferable.

R in OR is a hydrocarbon group, and the hydrocarbon group preferably includes an alkyl group, an aralkyl group, an aryl group and the like, preferably an alkyl group having 1 to 20 carbon atoms, an aralkyl group having 7 to 20 carbon atoms and an aryl group having 6 to 20 carbon atoms. Specific examples thereof include the same groups as described above.

Examples of R more preferably include a methyl group, an ethyl group, an isopropyl group, a tert-butyl group, an isobutyl group, a phenyl group, a 2,6-di(tert-butyl)phenyl group and benzyl group, further preferably a methyl group, a phenyl group, a 2,6-di(tert-butyl)phenyl group and benzyl group, most preferably a phenyl group.

Examples of more preferable X^1 include a chlorine atom, a methyl group, an ethyl group, a n-propyl group, an isopropyl group, a n-butyl group, a benzyl group, an allyl group and methallyl group.

In the formula [3], a is a number satisfying $0 < a \leq 8$,

b is a number satisfying $0 < b \leq 8$, and both are appropriately selected depending on a valence of M.

In the transition metal compound represented by the formula [3], specific examples of those having a titanium atom, a zirconium atom or a hafnium metal as the transition metal atom are bis(cyclopentadienyl)titanium dichloride, bis(methylcyclopentadienyl)titanium dichloride, bis(n-butylcyclopentadienyl)titanium dichloride, bis(dimethylcyclopentadienyl)titanium dichloride, bis(ethylmethylcyclopentadienyl)titanium dichloride, bis(trimethylcyclopentadienyl)titanium dichloride, bis(tetramethylcyclopentadienyl)titanium dichloride, bis(pentamethylcyclopentadienyl)titanium dichloride, bis-(indenyl)titanium dichloride, bis(4,5,6,7-tetrahydroindenyl)titanium dichloride, bis(fluorenyl)titanium dichloride, bis(2-phenylindenyl)titanium dichloride, bis[2-(bis-3,5-trifluoromethylphenyl)indenyl]titanium dichloride, bis[2-(4-tert-butylphenyl)indenyl]titanium dichloride, bis[2-(4-trifluoromethylphenyl)indenyl]titanium dichloride, bis[2-(4-methylphenyl)indenyl]titanium dichloride, bis[2-(3,5-dimethylphenyl)indenyl]titanium dichloride, bis[2-(pentafluorophenyl)indenyl]titanium dichloride, cyclopentadienyl(pentamethylcyclopentadienyl)-titanium dichloride, cyclopentadienyl(indenyl)titanium dichloride, cyclopentadienyl(fluorenyl)titanium dichloride, indenyl(fluorenyl)titanium dichloride, pentamethylcyclopentadienyl(indenyl)titanium dichloride, pentamethylcyclopentadienyl(fluorenyl)titanium dichloride,

cyclopentadienyl(2-phenylindenyl)titanium dichloride,
pentamethylcyclopentadienyl(2-phenylindenyl)titanium
dichloride, dimethylsilylenebis(cyclopentadienyl)titanium
dichloride,

5 dimethylsilylenebis(2-methylcyclopentadienyl)titanium
dichloride, dimethylsilylenebis(3-methylcyclopentadienyl)
titanium dichloride, dimethylsilylenebis(2-n-butylcyclo
pentadienyl)titanium dichloride,
dimethylsilylenebis(3-n-butylcyclopentadienyl)titanium
10 dichloride, dimethylsilylenebis(2,3-dimethylcyclo
pentadienyl)titanium dichloride,
dimethylsilylenebis(2,4-dimethylcyclopentadienyl)titanium
dichloride,
dimethylsilylenebis(2,5-dimethylcyclopentadienyl)titanium
15 dichloride,
dimethylsilylenebis(3,4-dimethylcyclopentadienyl)titanium
dichloride,
dimethylsilylenebis(2,3-ethylmethylcyclopentadienyl)
titanium dichloride, dimethylsilylenebis(2,4-ethylmethyl
20 cyclopentadienyl)titanium dichloride, dimethylsilylenebis(2,
5-ethylmethylcyclopentadienyl)titanium dichloride, dimethyl
silylenebis(3,5-ethylmethylcyclopentadienyl)titanium
dichloride,
dimethylsilylenebis(2,3,4-trimethylcyclopentadienyl)
25 titanium dichloride, dimethylsilylenebis(2,3,5-trimethyl
cyclopentadienyl)titanium dichloride, dimethylsilylenebis
(tetramethylcyclopentadienyl)titanium dichloride, dimethyl
silylenebis(indenyl)titanium dichloride, dimethyl
silylenebis(2-methylindenyl)titanium dichloride, dimethyl

silylenebis(2-tert-butylindenyl)titanium dichloride,
 dimethyl silylenebis(2,3-dimethylindenyl)titanium
 dichloride, dimethyl
 silylenebis(2,4,7-trimethylindenyl)titanium dichloride,
 5 dimethyl silylenebis(2-methyl-4-isopropylindenyl)titanium
 dichloride, dimethyl silylenebis(4,5-benzindenyl)titanium
 dichloride, dimethyl
 silylenebis(2-methyl-4,5-benzindenyl)titanium dichloride,
 dimethyl silylenebis(2-phenylindenyl)titanium dichloride,
 10 dimethyl silylenebis(4-phenylindenyl)titanium dichloride,
 dimethyl silylenebis(2-methyl-4-phenylindenyl)titanium
 dichloride, dimethyl silylenebis(2-methyl-5-
 phenylindenyl)titanium dichloride,
 dimethyl silylenebis(2-methyl-4-naphtylindenyl)titanium
 15 dichloride, dimethylsilylene
 bis(4,5,6,7-tetrahydroindenyl)titanium dichloride,
 dimethylsilylene(cyclopentadienyl)(indenyl)titanium
 dichloride, dimethylsilylene(methylcyclopentadienyl)
 (indenyl)titanium dichloride, dimethylsilylene(n-butylcyclo
 20 pentadienyl)(indenyl)titanium dichloride, dimethylsilylene
 (tetramethylcyclopentadienyl)(indenyl)titanium dichloride,
 dimethylsilylene(cyclopentadienyl)(fluorenyl)titanium
 dichloride,
 dimethylsilylene(methylcyclopentadienyl)(fluorenyl)
 25 titanium dichloride, dimethylsilylene(n-butylcyclo
 pentadienyl)(fluorenyl)titanium dichloride, dimethyl
 silylene(tetramethylcyclopentadienyl)(indenyl)titanium
 dichloride, dimethylsilylene(indenyl)(fluorenyl)titanium
 dichloride, dimethylsilylene(fluorenyl)titanium dichloride,

dimethylsilylene(cyclopentadienyl)
 (tetramethylcyclopentadienyl)titanium dichloride,
 dimethylsilylene(tetramethylcyclopentadienyl)(fluorenyl)ti
 tanium dichloride, cyclopentadienyltitanium trichloride,
 5 pentamethylcyclopentadienyltitanium trichloride,
 cyclopentadienyl(dimethylamide)titanium dichloride, cyclo
 pentadienyl(phenoxy)titanium dichloride, cyclopentadienyl(2,
 6-dimethylphenyl)titanium dichloride,
 cyclopentadienyl(2,6-diisopropylphenyl)titanium dichloride,
 10 cyclopentadienyl(2,6-di-tert-butylphenyl)titanium
 dichloride, pentamethylcyclopentadienyl(2,6-dimethylphenyl)
 titanium dichloride,
 pentamethylcyclopentadienyl(2,6-diisopropylphenyl)titanium
 dichloride,
 15 pentamethylcyclopentadienyl(2,6-tert-butylphenyl)titanium
 dichloride, indenyl(2,6-diisopropylphenyl)titanium
 dichloride, fluorenyl(2,6-diisopropylphenyl)titanium
 dichloride,
 dimethylsilylene(cyclopentadienyl)(2-phenoxy)titanium
 20 dichloride, dimethylsilylene(cyclopentadienyl)(3-methyl-2-
 phenoxy)titanium dichloride, dimethylsilylene(cyclo-
 pentadienyl)(3,5-dimethyl-2-phenoxy)titanium dichloride,
 dimethylsilylene(cyclopentadienyl)(3-tert-butyl-2-phenoxy)
 titanium dichloride, dimethylsilylene(cyclopentadienyl)
 25 (3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride,
 dimethylsilylene(cyclopentadienyl)(3, 5-di-tert-butyl-2-
 phenoxy)titanium dichloride, dimethylsilylene(cyclo-
 pentadienyl)(5-methyl-3-phenyl-2-phenoxy)titanium
 dichloride, dimethylsilylene(cyclopentadienyl)(3-tert-

butyldimethylsilyl-5-methyl-2-phenoxy)titanium dichloride,
 dimethylsilylene(cyclopentadienyl)(5-methyl-3-trimethyl-
 silyl-2-phenoxy)titanium dichloride, dimethylsilylene-
 (cyclopentadienyl)(3-tert-butyl-5-methoxy-2-phenoxy)
 5 titanium dichloride, dimethylsilylene(cyclopentadienyl)
 (3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride,
 dimethylsilylene(cyclopentadienyl)(3,5-diamyl-2-phenoxy)
 titanium dichloride,
 dimethylsilylene(cyclopentadienyl)(3-phenyl-2-phenoxy)
 10 titanium dichloride,
 dimethylsilylene(cyclopentadienyl)(1-naphtoxy-2-yl)
 titanium dichloride,
 dimethylsilylene(methylcyclopentadienyl)(2-phenoxy)
 titanium dichloride, dimethylsilylene(methylcyclo-
 15 pentadienyl)(3-methyl-2-phenoxy)titanium dichloride,
 dimethylsilylene(methylcyclopentadienyl)(3,5-dimethyl-2-
 phenoxy)titanium dichloride, dimethylsilylene(methyl-
 cyclopentadienyl)(3-tert-butyl-2-phenoxy)titanium
 dichloride, dimethylsilylene(methylcyclopentadienyl)
 20 (3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride,
 dimethylsilylene(methylcyclopentadienyl)(3,5-di-tert-
 butyl-2-phenoxy)titanium dichloride, dimethylsilylene
 (methylcyclopentadienyl)(5-methyl-3-phenyl-2-phenoxy)
 titanium dichloride, dimethylsilylene(methylcyclo-
 25 pentadienyl)(3-tert-butyldimethylsilyl-5-methyl-2-phenoxy)
 titanium dichloride, dimethylsilylene(methylcyclo-
 pentadienyl)(5-methyl-3-trimethylsilyl-2-phenoxy)titanium
 dichloride, dimethylsilylene(methylcyclopentadienyl)
 (3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride,

dimethylsilylene(methylcyclopentadienyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, dimethylsilylene(methylcyclopentadienyl)(3,5-diamyl-2-phenoxy)titanium dichloride, dimethylsilylene(methylcyclopentadienyl)(3-phenyl-2-phenoxy) titanium dichloride,
 5 dimethylsilylene(methylcyclopentadienyl)(1-naphtoxy-2-yl) titanium dichloride,
 dimethylsilylene(n-butylcyclopentadienyl)(2-phenoxy) titanium dichloride, dimethylsilylene(n-butylcyclopentadienyl)(3-methyl-2-phenoxy)titanium dichloride,
 10 dimethylsilylene(n-butylcyclopentadienyl)(3,5-dimethyl-2-phenoxy)titanium dichloride, dimethylsilylene(n-butylcyclopentadienyl)(3-tert-butyl-2-phenoxy) titanium dichloride, dimethylsilylene(n-butylcyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride,
 15 dimethylsilylene(n-butylcyclopentadienyl)(3,5-di-tert-butyl-2-phenoxy)titanium dichloride, dimethylsilylene(n-butylcyclopentadienyl)(5-methyl-3-phenyl-2-phenoxy) titanium dichloride, dimethylsilylene(n-butylcyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride,
 20 dimethylsilylene(n-butylcyclopentadienyl)(5-methyl-3-trimethylsilyl-2-phenoxy)titanium dichloride, dimethylsilylene(n-butylcyclopentadienyl)(3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride,
 25 dimethylsilylene(n-butylcyclopentadienyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, dimethylsilylene(n-butylcyclopentadienyl)(3,5-diamyl-2-phenoxy)titanium dichloride,
 dimethylsilylene(n-butylcyclopentadienyl)(3-phenyl-2-phenoxy)titanium dichloride,

xy) titanium dichloride,
 dimethylsilylene(n-butylcyclopentadienyl)(1-naphthoxy-2-yl)
 titanium dichloride,
 dimethylsilylene(tert-butylcyclopentadienyl)(2-phenoxy)
 5 titanium dichloride, dimethylsilylene(tert-butylcyclo-
 pentadienyl)(3-methyl-2-phenoxy)titanium dichloride,
 dimethylsilylene(tert-butylcyclopentadienyl)(3,5-dimethyl-
 2-phenoxy)titanium dichloride, dimethylsilylene(tert-butyl-
 cyclopentadienyl)(3-tert-butyl-2-phenoxy)titanium
 10 dichloride, dimethylsilylene(tert-butylcyclopentadienyl)
 (3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride,
 dimethylsilylene(tert-butylcyclopentadienyl)(3,5-di-tert-
 butyl-2-phenoxy)titanium dichloride, dimethylsilylene
 (tert-butylcyclopentadienyl)(5-methyl-3-phenyl-2-phenoxy)
 15 titanium dichloride, dimethylsilylene(tert-butylcyclo-
 pentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)
 titanium dichloride, dimethylsilylene(tert-butylcyclo-
 pentadienyl)(5-methyl-3-trimethylsilyl-2-phenoxy)titanium
 dichloride, dimethylsilylene(tert-butylcyclopentadienyl)
 20 (3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride,
 dimethylsilylene(tert-butylcyclopentadienyl)(3-tert-butyl-
 5-chloro-2-phenoxy)titanium dichloride, dimethylsilylene
 (tert-butylcyclopentadienyl)(3,5-diamyl-2-phenoxy) titanium
 dichloride,
 25 dimethylsilylene(tert-butylcyclopentadienyl)(3-phenyl-2-ph
 enoxy) titanium dichloride,
 dimethylsilylene(tert-butylcyclopentadienyl)(1-naphthoxy-2-
 yl) titanium dichloride,
 dimethylsilylene(tetramethylcyclopentadienyl)(2-phenoxy)

titanium dichloride, dimethylsilylene(tetramethylcyclopentadienyl)(3-methyl-2-phenoxy)titanium dichloride,
 dimethylsilylene(tetramethylcyclopentadienyl)(3,5-dimethyl-2-phenoxy)titanium dichloride, dimethylsilylene(tetramethylcyclopentadienyl)(3-tert-butyl-2-phenoxy)titanium
 5 dichloride, dimethylsilylene(tetramethylcyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride,
 dimethylsilylene(tetramethylcyclopentadienyl)(3,5-di-tert-butyl-2-phenoxy) titanium dichloride, dimethylsilylene
 10 (tetramethylcyclopentadienyl)(5-methyl-3-phenyl-2-phenoxy) titanium dichloride, dimethylsilylene(tetramethylcyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy) titanium dichloride,
 dimethylsilylene(tetramethylcyclopentadienyl)(5-methyl-3-trimethylsilyl-2-phenoxy)titanium
 15 dichloride, dimethylsilylene(tetramethylcyclopentadienyl)(3-tert-butyl-5-methoxy-2-phenoxy)titanium dichloride,
 dimethylsilylene(tetramethylcyclopentadienyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium dichloride, dimethylsilylene(tetramethylcyclopentadienyl)(3,5-diamyl-2-
 20 phenoxy)titanium dichloride,
 dimethylsilylene(tetramethylcyclopentadienyl)(3-phenyl-2-phenoxy) titanium dichloride,
 dimethylsilylene(tetramethylcyclopentadienyl)(1-naphthoxy-2-yl) titanium dichloride,
 25 dimethylsilylene(trimethylsilylcyclopentadienyl)(2-phenoxy)titanium dichloride, dimethylsilylene
 (trimethylsilylcyclopentadienyl)(3-methyl-2-phenoxy) titanium dichloride, dimethylsilylene(trimethylsilylcyclopentadienyl)(3,5-dimethyl-2-phenoxy)titanium dichloride,

dimethylsilylene(trimethylsilylcyclopentadienyl)(3-tert-butyl-2-phenoxy)titanium dichloride, dimethylsilylene
 (trimethylsilylcyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium dichloride, dimethylsilylene(trimethyl-
 5 silylcyclopentadienyl)(3,5-di-tert-butyl-2-phenoxy)
 titanium dichloride, dimethylsilylene(trimethylsilylcyclo-
 pentadienyl)(5-methyl-3-phenyl-2-phenoxy)titanium
 dichloride, dimethylsilylene(trimethylsilylcyclo-
 pentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)
 10 titanium dichloride, dimethylsilylene(trimethylsilylcyclo-
 pentadienyl)(5-methyl-3-trimethylsilyl-2-phenoxy)titanium
 dichloride, dimethylsilylene(trimethylsilylcyclo-
 pentadienyl)(3-tert-butyl-5-methoxy-2-phenoxy)titanium
 dichloride, dimethylsilylene(trimethylsilylcyclo-
 15 pentadienyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium
 dichloride, dimethylsilylene(trimethylsilylcyclo-
 pentadienyl)(3,5-diamyl-2-phenoxy)titanium dichloride,
 dimethylsilylene(trimethylsilylcyclopentadienyl)(3-phenyl-
 2-phenoxy) titanium dichloride,
 20 dimethylsilylene(trimethylsilylcyclopentadienyl)(1-naphtox
 y-2-yl) titanium dichloride,
 dimethylsilylene(indenyl)(2-phenoxy)titanium dichloride,
 dimethylsilylene(indenyl)(3-methyl-2-phenoxy) titanium
 dichloride, dimethylsilylene(indenyl)(3,5-dimethyl-2-
 25 phenoxy)titanium dichloride, dimethylsilylene(indenyl)
 (3-tert-butyl-2-phenoxy)titanium dichloride, dimethyl-
 silylene(indenyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium
 dichloride, dimethylsilylene(indenyl)(3,5-di-tert-butyl-2-
 phenoxy)titanium dichloride, dimethylsilylene(indenyl)

(5-methyl-3-phenyl-2-phenoxy)titanium dichloride,
 dimethylsilylene(indenyl)(3-tert-butyl dimethylsilyl-5-
 methyl-2-phenoxy)titanium dichloride, dimethylsilylene
 (indenyl)(5-methyl-3-trimethylsilyl-2-phenoxy)titanium
 5 dichloride, dimethylsilylene(indenyl)(3-tert-butyl-5-
 methoxy-2-phenoxy)titanium dichloride, dimethylsilylene
 (indenyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium
 dichloride, dimethylsilylene(indenyl)(3,5-diamyl-2-phenoxy)
 titanium dichloride,
 10 dimethylsilylene(indenyl)(3-phenyl-2-phenoxy) titanium
 dichloride, dimethylsilylene(indenyl)(1-naphtoxy-2-yl)
 titanium dichloride,
 dimethylsilylene(fluorenyl)(2-phenoxy)titanium dichloride,
 dimethylsilylene(fluorenyl)(3-methyl-2-phenoxy)titanium
 15 dichloride, dimethylsilylene(fluorenyl)(3,5-dimethyl-2-
 phenoxy)titanium dichloride, dimethylsilylene(fluorenyl)
 (3-tert-butyl-2-phenoxy)titanium dichloride, dimethyl-
 silylene(fluorenyl)(3-tert-butyl-5-methyl-2-phenoxy)
 titanium dichloride, dimethylsilylene(fluorenyl)(3,5-di-
 20 tert-butyl-2-phenoxy)titanium dichloride, dimethylsilylene
 (fluorenyl)(5-methyl-3-phenyl-2-phenoxy)titanium dichloride,
 dimethylsilylene(fluorenyl)(3-tert-butyl dimethylsilyl-5-
 methyl-2-phenoxy)titanium dichloride, dimethylsilylene
 (fluorenyl)(5-methyl-3-trimethylsilyl-2-phenoxy)titanium
 25 dichloride, dimethylsilylene(fluorenyl)(3-tert-butyl-5-
 methoxy-2-phenoxy)titanium dichloride, dimethylsilylene
 (fluorenyl)(3-tert-butyl-5-chloro-2-phenoxy)titanium
 dichloride, dimethylsilylene(fluorenyl)(3,5-diamyl-2-
 phenoxy)titanium dichloride,

dimethylsilylene(fluorenyl)(3-phenyl-2-phenoxy) titanium
 dichloride, dimethylsilylene(fluorenyl)(1-naphtoxy-2-yl)
 titanium dichloride,
 (tert-butylamide)tetramethylcyclopentadienyl-1,2-ethanedi-
 5 yl titanium dichloride, (methylamide)tetramethylcyclopenta-
 dienyl-1,2-ethanediyl titanium dichloride, (ethylamide)
 tetramethylcyclopentadienyl-1,2-ethanediyl titanium
 dichloride, (tert-butylamide)tetramethylcyclopentadienyl-
 dimethylsilane titanium dichloride,
 10 (benzylamide)tetramethyl-cyclopentadienyldimethylsilane
 titanium dichloride,
 (phenylphosphide)tetramethylcyclopentadienyldimethylsilane
 titanium dichloride,
 (tert-butylamide)indenyl-1,2-ethanediyl titanium dichloride,
 15 (tert-butylamide)tetrahydroindenyl-1,2-ethanediyltitanium
 dichloride, (tert-butylamide)fluorenyl-1,2-ethanediyl
 titanium dichloride, (tert-butylamide)indenyl dimethylsilane
 titanium dichloride,
 (tert-butylamide)tetrahydroindenyl dimethylsilane titanium
 20 dichloride, (tert-butylamide)fluorenyldimethylsilane
 titanium dichlorede,
 (dimethylaminomethyl)tetramethylcyclopentadienyl titanium
 (III) dichloride, (dimethylaminoethyl)tetramethyl
 cyclo-pentadienyl titanium(III) dichloride,
 25 (dimethylaminopropyl) tetramethylcyclopentadienyl
 titanium(III) dichloride,
 (N-pyrrolidinyethyl)tetramethylcyclopentadienyl titanium
 dichloride, (B-dimethylaminoborabenzene)cyclopentadienyl-
 titanium dichloride,

cyclopentadienyl(9-mesitylboraanthracenyl) titanium
dichloride,
2,2'-thiobis[4-methyl-6-tert-butylphenoxy]titanium
dichloride, 2,2'-thiobis[4-methyl-6-(1-methylethyl)
5 phenoxy]titanium dichloride, 2,2'-thiobis(4,6-dimethyl
phenoxy)titanium dichloride,
2,2'-thiobis(4-methyl-6-tert-butylphenoxy)titanium
dichloride, 2,2'-methylenebis(4-methyl-6-tert-butyl
phenoxy)titanium dichloride,
10 2,2'-ethylenebis(4-methyl-6-tert-butylphenoxy)titanium
dichloride, 2,2'-sulfinylbis(4-methyl-6-tert-butylphenoxy)
titanium dichloride, 2,2'-(4,4',6,6'-tetra-tert-butyl-1,1'-
biphenoxy)titanium dichloride,
(di-tert-butyl-1,3-propanediamide)titanium dichloride,
15 (dicyclohexyl-1,3-propanediamide) titanium dichloride,
[bis(trimethylsilyl)-1,3-propanedidiamide]titanium
dichloride, [bis(tert-butyl dimethylsilyl)-1,3-propane-
diamide]titanium dichloride, [bis(2,6-dimethylphenyl)-1,3-
propanediamide]titanium dichloride, [bis(2,6-diisopropyl-
20 phenyl)-1,3-propanediamide]titanium dichloride,
[bis(2,6-di-tert-butylphenyl)-1,3-propanediamide]titanium
dichloride, [bis(triisopropylsilyl)naphthalenediamide]
titanium dichloride, [bis(trimethylsilyl)naphthalene-
diamide]titanium dichloride, [bis(tert-butyl dimethylsilyl)
25 naphthalenediamide]titanium dichloride,
[hydrotris(3,5-dimethylpyrazolyl)borate]titanium
trichloride, [hydrotris(3,5-diethylpyrazolyl)
-borate]titanium trichloride,
[hydrotris(3,5-di-tert-butylpyrazolyl)borate]titanium

trichloride, [tris(3,5-dimethylpyrazolyl)methyl]titanium
trichloride, [tris(3,5-diethylpyrazolyl)methyl]titanium
trichloride, [tris(3,5-di-tert-butylpyrazolyl)methyl]
titanium trichloride, and those formed by replacing the titanium
5 of these compounds with zirconium or hafnium, those formed by
replacing the 2-phenoxy of these compounds with
(3-phenyl-2-phenoxy), (3-trimethylsilyl-2-
phenoxy) or (3-tert-butyl dimethylsilyl-2-phenoxy), those
formed by replacing the dimethylsilylene of these compounds
10 with methylene, ethylene, dimethylmethylene(isopropylidene),
diphenylmethylene, diethylsilylene, diphenylsilylene or
dimethoxysilylene, those formed by replacing the dichloride
of these compounds with difluoride, dibromide, diiodide,
dimethyl, diethyl, diisopropyl, diphenyl, dibenzyl,
15 dimethoxide, diethoxide, di-n-propoxide, diisopropoxide,
di-n-butoxide, diisobutoxide, di-tert-butoxide, diphenoxide
or di(2,6-di-tert-butylphenoxide), and those formed by
replacing the trichloride of these compounds with trifluoride,
tribromide, triiodide, trimethyl, triethyl, triisopropyl,
20 triphenyl, tribenzyl, trimethoxide, triethoxide,
tri-n-propoxide, triisopropoxide, tri-n-butoxide,
triisobutoxide, tri-tert-butoxide, triphenoxide or
tri(2,6-di-tert-butylphenoxide).

In the transition metal compounds represented by the
25 formula [3], specific examples of a compound having a nickel
atom as a transition metal atom are
2,2'-methylenebis[(4R)-4-phenyl-5,5'-dimethyloxazoline]
nickel dibromide, 2,2'-methylenebis[(4R)-4-phenyl
-5,5'-diethyloxazoline] nickel dibromide,

2,2'-methylenebis[(4R)-4-phenyl-5,5'-di-n-propyloxazoline]
 nickel dibromide,
 2,2'-methylenebis[(4R)-4-phenyl-5,5'-diisopropyloxazoline]
 nickel dibromide,
 5 2,2'-methylenebis[(4R)-4-phenyl-5,5'-dicyclohexyloxazoline
] nickel dibromide,
 2,2'-methylenebis[(4R)-4-phenyl-5,5'-dimethoxyoxazoline]
 nickel dibromide,
 2,2'-methylenebis[(4R)-4-phenyl-5,5'-diethoxyoxazoline]
 10 nickel dibromide,
 2,2'-methylenebis[(4R)-4-phenyl-5,5'-diphenyloxazoline]
 nickel dibromide,
 2,2'-methylenebis[(4R)-4-methyl-5,5'-di-(2-methylphenyl)ox
 azoline]nickel dibromide,
 15 2,2'-methylenebis[(4R)-4-methyl-5,5-di-(3-methylphenyl)
 oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-methyl-5,5-di-(4-methylphenyl)
 oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-methyl-5,5-di-(2-methoxyphenyl)
 20 oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-methyl-5,5-di-(3-methoxyphenyl)
 oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-methyl-5,5-di-(4-methoxyphenyl)
 oxazoline]nickel dibromide, 2,2'-methylenebis[spiro{(4R)-4-
 25 methyloxazoline-5,1'-cyclobutane}]nickel dibromide,
 2,2'-methylenebis[spiro{(4R)-4-methyloxazoline-5,1'-
 cyclopentane}]nickel dibromide,
 2,2'-methylenebis[spiro{(4R)-4-methyloxazoline-5,1'-cycloh
 exane}] nickel dibromide,

2,2'-methylenebis[spiro{(4R)-4-methyloxazoline-5,1'-cyclo
 heptane}]nickel dibromide,
 2,2'-methylenebis[(4R)-4-isopropyl-5,5-dimethyloxazoline]
 nickel dibromide, 2,2'-methylenebis [(4R)-4-isopropyl-
 5 5,5-diethyloxazoline]nickel dibromide, 2,2'-methylenebis
 [(4R)-4-isopropyl-5,5-di-n-propyloxazoline], methylenebis
 [(4R)-4-isopropyl-5,5-diisopropyloxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-isopropyl-5,5-dicyclohexyloxazoli
 ne]nickel dibromide,
 10 2,2'-methylenebis[(4R)-4-isopropyl-5,5-diphenyloxazoline]
 nickel dibromide,
 2,2'-methylenebis[(4R)-4-isopropyl-5,5-di-(2-methylphenyl)
 oxazoline]nickel dibromide, 2,2'-methylenebis[(4R)-4-
 isopropyl-5,5-di-(3-methylphenyl)oxazoline]nickel dibromide,
 15 2,2'-methylenebis[(4R)-4-isopropyl-5,5-di-(4-methylphenyl)
 oxazoline]nickel dibromide, 2,2'-methylenebis[(4R)-4-
 isopropyl-5,5-di-(2-methoxyphenyl)oxazoline]nickel
 dibromide, 2,2'-methylenebis[(4R)-4-isopropyl-5,5-
 di-(3-methoxyphenyl)oxazoline]nickel dibromide,
 20 2,2'-methylenebis[(4R)-4-isopropyl-5,5-di-(4-methoxyphenyl
)oxazoline]nickel dibromide,
 2,2'-methylenebis[spiro{(4R)-4-isopropyloxazoline-5,1'-
 cyclobutane}]nickel dibromide,
 2,2'-methylenebis[spiro{(4R)-4-isopropyl-oxazoline-5,1'-
 25 cyclopentane}]nickel dibromide,
 2,2'-methylenebis[spiro{(4R) -4-isopropyloxazoline-5,1'-
 cyclohexane}]nickel dibromide,
 2,2'-methylenebis[spiro{(4R)-4-isopropyloxazoline-5,1'-
 cycloheptane}]nickel dibromide,

2,2-methylenebis[(4R)-4-isobutyl-5,5-dimethyloxazoline]
 nickel dibromide,
 2,2'-methylenebis[(4R)-4-isobutyl-5,5-diethyloxazoline]
 nickel dibromide,
 5 2,2'-methylenebis[(4R)-4-isobutyl-5,5-di-n-propyloxazoline
]nickel dibromide,
 2,2'-methylenebis[(4R)-4-isobutyl-5,5-di-isopropyloxazolin
 e]nickel dibromide,
 2,2'-methylenebis[(4R)-4-isobutyl-5,5-dicyclohexyloxazolin
 10 e]nickel dibromide,
 2,2'-methylenebis[(4R)-4-isobutyl-5,5-diphenyloxazoline]
 nickel dibromide,
 2,2'-methylenebis[(4R)-4-isobutyl-5,5-di-(2-methylphenyl)
 oxazoline]nickel dibromide,
 15 2,2'-methylenebis[(4R)-4-isobutyl-5,5-di-(3-methylphenyl)
 oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-isobutyl-5,5-di-(4-methylphenyl)o
 xazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-isobutyl-5,5-di-(2-methoxyphenyl)
 20 oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-isobutyl-5,5-di-(3-methoxyphenyl)
 -oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-isobutyl-5,5-di-(4-methoxyphenyl)
 oxazoline]nickel dibromide, 2,2'-methylenebis
 25 [spiro{(4R)-4-isobutyloxazoline-5,1'-cyclobutane}]nickel
 dibromide,
 2,2'-methylenebis[spiro{(4R)-4-isobutyloxazoline-5,1'-cycl
 opentane}]nickel dibromide,
 2,2'- methylenebis[spiro{(4R)-4-isobutyloxazoline-5,1'-

cyclohexane}}nickel dibromide,
 2,2'-methylenebis[spiro{(4R)-4-isobutyloxazoline-5,1'-
 cycloheptane}}nickel dibromide,
 2,2'-methylenebis[(4R)-4-tert-butyl-5,5-dimethyloxazoline]
 5 nickel dibromide, 2,2'-methylenebis[(4R)-4-tert-butyl
 -5,5-diethyloxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-4-tert-butyl-5,5-di-n-propyl
 oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-tert-butyl-5,5-di-isopropyl-
 10 oxazoline]nickel dibromide, 2,2'-methylenebis[(4R)-4-tert-
 butyl-5,5-diphenyloxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-tert-butyl-5,5-dicyclohexyl
 oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-tert-butyl-5,5-di-(2-methyl
 15 phenyl)oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-tert-butyl-5,5-di-(3-methyl
 phenyl)oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-tert-butyl-5,5-di-(4-methyl
 phenyl)oxazoline]nickel dibromide,
 20 2,2'-methylenebis[(4R)-4-tert-butyl-5,5-di-(2-methoxy
 phenyl)oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-tert-butyl-5,5-di-(3-methoxy
 phenyl)oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-tert-butyl-5,5-di-(4-methoxy
 25 phenyl)oxazoline]nickel dibromide,
 2,2'-methylenebis[spiro(4R)-4-tertbutyloxazoline-5,1'-
 cyclobutane}}nickel dibromide,
 2,2'-methylenebis[spiro{(4R)-4-tert-butyloxazoline-5,1'-
 cyclopentane}}nickel dibromide,


2,2'-methylenebis[spiro{(4R)-4-tert-butyloxazoline-5,1'-
 cyclohexane}]nickel dibromide,
 2,2'-methylenebis[spiro{(4R)-4-tert-butyloxazoline-5,1'-
 cycloheptane}]nickel dibromide,
 5 2,2'-methylenebis[(4R)-4-phenyl-5,5-dimethyloxazoline]
 nickel dibromide,
 2,2'-methylenebis[(4R)-4-phenyl-5,5-diethyloxazoline]
 nickel dibromide,
 2,2'-methylenebis[(4R)-4-phenyl-5,5-di-n-propyloxazoline]
 10 nickel dibromide,
 2,2'-methylenebis[(4R)-4-phenyl-5,5-di-isopropyloxazoline]
 nickel dibromide,
 2,2'-methylenebis[(4R)-4-phenyl-5,5-dicyclohexyloxazoline]
 nickel dibromide,
 15 2,2'-methylenebis(4R)-4-phenyl-5,5-diphenyloxazoline]
 nickel dibromide,
 2,2'-methylenebis[(4R)-4-phenyl-5,5-di-(2-methylphenyl)
 oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-phenyl-5,5-di-(3-methylphenyl)
 20 oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-phenyl-5,5-di-(4-methylphenyl)
 oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4--phenyl-5,5-di-(2-methoxyphenyl)
 oxazoline]nickel dibromide,
 25 2,2'-methylenebis[(4R)-4-phenyl-5,5-di-(3-methoxyphenyl)
 oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4--phenyl-5,5-di-(4-methoxyphenyl)
 oxazoline]nickel dibromide,
 2,2'-methylenebis[spiro{(4R)-4-phenyloxazoline-5,1'-

cyclobutane}]nickel dibromide,
 2,2'-methylenebis[spiro{(4R)-4-phenyloxazoline-5,1'-
 cyclopentane}]nickel dibromide,
 2,2'-methylenebis[spiro{(4R)-4-phenyloxazoline-5,1'-
 5 cyclohexane}] nickel dibromide,
 2,2'-methylenebis[spiro{(4R)-4-phenyloxazoline-5,1'-
 cycloheptane}]nickel dibromide,
 2,2'-methylenebis[(4R)-4-benzyl-5,5-dimethyloxazoline]
 nickel dibromide,
 10 2,2'-methylenebis[(4R)-4-benzyl-5,5-diethyloxazoline]
 nickel dibromide,
 2,2'-methylenebis[(4R)-4-benzyl-5,5-di-n-propyloxazoline]
 nickel dibromide,
 2,2'-methylenebis[(4R)-4-benzyl-5,5-di-isopropyloxazoline]
 15 nickel dibromide,
 2,2'-methylenebis[(4R)-4-benzyl-5,5-dicyclohexyloxazoline]
 nickel dibromide,
 2,2'-methylenebis[(4R)-4-benzyl-5,5-diphenyloxazoline]
 nickel dibromide,
 20 2,2'-methylenebis[(4R)-4-benzyl-5,5-di-(2-methylphenyl)
 oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-benzyl-5,5-di-(3-methylphenyl)
 oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-benzyl-5,5-di-(4-methylphenyl)
 25 oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-benzyl-5,5-di-(2-methoxyphenyl)
 oxazoline]nickel dibromide,
 2,2'-methylenebis[(4R)-4-benzyl-5,5-di-(3-methoxyphenyl)
 oxazoline]nickel dibromide,

2,2'-methylenebis[(4R)-4-benzyl-5,5-di-(4-methoxyphenyl)oxazoline]nickel dibromide,
 2,2'-methylenebis[spiro{(4R)-4-benzyloxazoline-5,1'-cyclobutane}]nickel dibromide,
 5 2,2'-methylenebis[spiro{(4R)-4-benzyloxazoline-5,1'-cyclopentane}]nickel dibromide,
 2,2'-methylenebis[spiro{(4R)-4-benzyloxazoline-5,1'-cyclohexane}]nickel dibromide,
 2,2'-methylenebis[spiro{(4R)-4-benzyloxazoline-5,1'-cycloheptane}]nickel dibromide, and antidopes of the
 10 above-mentioned compounds. Further, there are exemplified those formed by reversing a steric configuration of the asymmetric carbon on one hand oxazoline ring of the above-mentioned bisoxazoline compound, and those formed by
 15 replacing the dibromide of said compounds with difluoride, dichloride, diiodide, dimethyl, diethyl, diisopropyl, diphenyl, dizenzyl, dimethoxide, diethoxide, di-n-propoxide, diisopropoxide, di-n-butoxide, diisobutoxide, di-tert-butoxide, diphenoxide or
 20 di(2,6-di-tert-butylphenoxide).

Further, specific examples of the nickel compound are [hydrotris(3,5-dimethylpyrazolyl)borate]nickel chloride, [hydrotris(3,5-diethylpyrazolyl)borate]nickel chloride, [hydrotris(3,5-di-tert-butylpyrazolyl)borate]nickel
 25 chloride and those formed by replacing the dichloride of said compounds with bromide, iodide, methyl, ethyl, allyl, metharyl, methoxide, ethoxide, n-propoxide, isopropoxide, n-butoxide, isobutoxide, tert-butoxide, phenoxide or 2,6-di-tert-butylphenoxide.

Further, compounds represented the following structural formula:



(in the formula, each of R⁴ and R⁵ is 2,6-diisopropylphenyl group; each of R⁶ and R⁷ is a hydrogen atom or methyl group, acenaphthene group in which R⁶ and R⁷ are combined; X² is a fluorine atom, a chlorine atom, a bromine atom, an iodine atom, a methyl group, an ethyl group, a n-propyl group, an isopropyl group, a n-butyl group, a phenyl group, a benzyl group, a methoxy group, an ethoxy group, a n-propoxy group, an isopropoxy group, a n-butoxy group, an isobutoxy group, or a phenoxy group; and more than one X² may be the same or different each other.) are illustrated.

Furthermore, there are exemplified compounds obtained by substituting nickel in the above-mentioned nickel compounds with palladium, cobalt, rhodium or ruthenium.

In the transition metal compound represented by the formula [3], specific examples of a compound having an iron atom as a transition metal atom are

2,6-bis-[1-(2,6-dimethylphenylimino)ethyl]pyridine iron dichloride, 2,6-bis-[1-(2,6-diisopropylphenylimino)ethyl]pyridine iron dichloride,

2,6-bis-[1-(2-tert-butyl-phenylimino)ethyl]pyridine iron dichloride, and compounds in which dichloride in those described above is replaced with difluoride, dibromide, diiodide, dimethyl, diethyl, dimethoxide, diethoxide, di-n-propoxide,

diisopropoxide, di-n-butoxide, diisobutoxide,
di-tert-butoxide, diphenoxide or
di(2,6-di-tert-butylphenoxide).

Still further, specific examples of the iron compound are
5 [hydrotris(3,5-dimethylpyrazolyl)borate]iron chloride,
[hydrotris(3,5-diethylpyrazolyl)borate]iron chloride,
[hydrotris(3,5-di-tert-butylpyrazolyl)borate]iron chloride
and those formed by replacing the dichloride of said compounds
with fluoride, bromide, iodide, methyl, ethyl, allyl, methallyl,
10 methoxide, ethoxide, n-propoxide, isopropoxide, n-butoxide,
isobutoxide, tert-butoxide, phenoxide or
2,6-di-tert-butylphenoxide.

Moreover, there are also similarly exemplified compounds,
which are formed by replacing iron in the above-mentioned
15 compounds with cobalt.

Examples of μ -oxo type transition metal compounds in the
transition metal compound represented by the formula [3] are
 μ -oxobis[isopropylidene(cyclopentadienyl)
(2-phenoxy)titanium chloride], μ -oxobis[isopropylidene
20 (cyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)
titanium chloride], μ -oxobis[isopropylidene(methylcyclo-
pentadienyl)(2-phenoxy)titanium chloride], μ -oxobis[iso-
propylidene(methylcyclopentadienyl)(3-tert-butyl-5-methyl-
2-phenoxy)titanium chloride], μ -oxobis[isopropylidene
25 (tetramethylcyclopentadienyl)(2-phenoxy)titanium chloride],
 μ -oxobis[isopropylidene(tetramethylcyclopentadienyl)
(3-tert-butyl-5-methyl-2-phenoxy)titanium chloride], μ -oxo-
bis[dimethylsilylene(cyclopentadienyl)(2-phenoxy)titanium
chloride], μ -oxobis[dimethylsilylene(cyclopentadienyl)

(3-tert-butyl-5-methyl-2-phenoxy)titanium chloride], μ -oxo-bis[dimethylsilylene(methylcyclopentadienyl)(2-phenoxy)titanium chloride], μ -oxobis[dimethylsilylene(methylcyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium chloride], μ -oxobis[dimethylsilylene(tetramethylcyclopentadienyl)(2-phenoxy)titanium chloride], and μ -oxobis[dimethylsilylene(tetramethylcyclopentadienyl)(3-tert-butyl-5-methyl-2-phenoxy)titanium chloride]. Further, compounds formed by replacing the chloride of the above-described μ -oxocompounds with fluoride, bromide, iodide, methyl, ethyl, isopropyl, phenyl, benzyl, methoxide, ethoxide, n-propoxide, isopropoxide, n-butoxide, isobutoxide, tert-butoxide, phenoxide or 2,6-di-tert-butylphenoxide.

Besides, the transition metal compound represented by the formula [3] and its μ -oxo type transition metal compound, whose examples are as mentioned above, examples of a compound used as the transition metal compound (B) are as follows. Examples of a compound having a nickel atom as the transition metal atom are nickel chloride, nickel bromide, nickel iodide, nickel sulfate, nickel nitrate, nickel perchlorate, nickel acetate, nickel trifluoroacetate, nickel cyanide, nickel oxalate, acetylacetonatonickel, bis(allyl)nickel, bis(1,5-cyclooctadiene)nickel, dichloro(1,5-cyclooctadiene)nickel, dichlorobis(acetonitrile)nickel, dichlorobis(benzonitrile)nickel, carbonyltris(triphenylphosphine)nickel, dichlorobis(triethylphosphine)nickel, diacetobis(triphenylphosphine)nickel,

tetraxis(triphenylphosphine)nickel,
dichloro[1,2-bis(diphenylphosphino)ethane]nickel,
bis[1,2-bis(diphenylphosphino)ethane]nickel,
dichloro[1,3-bis(diphenylphosphino)propane]nickel,
5 bis[1,3-bis(diphenylphosphino)propane]nickel,
tetraaminenickel nitrate, tetrakis(acetonitrile)nickel
tetrafluoroborate and nickelpthalocianine.

Similarly, examples of a compound having a vanadium atom
as the transition metal atom are vanadium acetylacetonate,
10 vanadium tetrachloride and vanadium oxytrichloride.

Example of a compound having a samarium atom as the transition
metal atom is bis(pentamethylcyclopentadienyl)samarium
methyltetrahydrofuran.

Example of a compound having an ytterbium atom as the
15 transition metal atom is bis(pentamethylcyclopentadienyl)
ytterbium methyltetrahydrofuran.

These transition metal compound may be used alone or
in combination of two or more kinds.

Among those transition metal compounds exemplified above,
20 those represented by the formula [3] are preferred as the
transition metal compound (B) used in the present invention.
In particular, the transition metal compounds having the 4 Group
atom as M in the above formula [3] are preferred, and those
having at least one cyclopentadiene type anion
25 skeleton-carrying group as L^2 in the formula [3] are particularly
preferred.

(C) Organoaluminum compound

As the organoaluminum compound of the component (C) used
for the catalyst for addition polymerization in accordance with

the present invention, a known organoaluminum compound can be used. Preferred is an organoaluminum compound represented by the following formula [6].



5 (In the formula, R^8 is a hydrocarbon group and all of R^8 may be the same or different from one another, Y is a hydrogen atom, a halogen atom, an alkoxy group, an aralkyloxy group, or an aryloxy group, all of Y may be the same or different from one another, and c is a number satisfying $0 < c \leq 3$.)

10 In the formula [6] representing the organoaluminum compound, as R^8 , preferred is a hydrocarbon group having 1 to 24 carbon atoms, and more preferred is an alkyl group having 1 to 24 carbon atoms. Specific examples thereof are a methyl group, an ethyl group, a n-propyl group, a n-butyl group, an
15 isobutyl group, a n-hexyl group, a 2-methylhexyl group and a n-octyl group. Preferred are an ethyl group, a n-butyl group, an isobutyl group, a n-hexyl group or an n-octyl group.

When Y is a halogen atom, specific examples thereof are a fluorine atom, a chlorine atom, a bromine atom and an iodine
20 atom, and preferred is a chlorine atom.

When Y is an alkoxy group, preferred is an alkoxy group having 1 to 24 carbon atoms. Specific examples thereof are a methoxy group, an ethoxy group, a n-propoxy group, an isopropoxy group, an n-butoxy group, a sec-butoxy group, a tert-butoxy group,
25 a n-pentoxy group, a neopentoxy group, a n-hexoxy group, a n-octoxy group, a n-dodecoxy group, a n-pentadecoxy group and a n-eicoxy group, and preferred are a methoxy group, an ethoxy group and a tert-butoxy group.

When Y is an aryloxy group, preferred is an aryloxy having

6 to 24 carbon atoms. Specific examples thereof are a phenoxy group, a 2-methylphenoxy group, a 3-methylphenoxy group, a 4-methylphenoxy group, a 2,3-dimethylphenoxy group, a 2,4-dimethylphenoxy group, a 2,5-dimethylphenoxy group, a 2,6-dimethylphenoxy group, a 3,4-dimethylphenoxy group, a 3,5-dimethylphenoxy group, a 2,3,4-trimethylphenoxy group, a 2,3,5-trimethylphenoxy group, a 2,3,6-trimethylphenoxy group, a 2,4,5-trimethylphenoxy group, a 2,4,6-trimethylphenoxy group, a 3,4,5-trimethylphenoxy group, a 2,3,4,5-tetramethylphenoxy group, a 2,3,4,6-tetramethylphenoxy group, a 2,3,5,6-tetramethylphenoxy group, a pentamethylphenoxy group, an ethylphenoxy group, a n-propylphenoxy group, an isopropylphenoxy group, a n-butylphenoxy group, a sec-butylphenoxy group, a tert-butylphenoxy group, a n-hexylphenoxy group, a n-octylphenoxy group, a n-decylphenoxy group, a n-tetradecylphenoxy group, a naphthoxy group and an anthracenoxy group.

When Y is an aralkyloxy group, preferred is an aralkyloxy having 7 to 24 carbon atoms. Specific examples thereof are a benzyloxy group, a (2-methylphenyl)methoxy group, a (3-methylphenyl)methoxy group, a (4-methylphenyl)methoxy group, a (2,3-dimethylphenyl)methoxy group, a (2,4-dimethylphenyl)methoxy group, a (2,5-dimethylphenyl)methoxy group, a (2,6-dimethylphenyl)methoxy group, a (3,4-dimethylphenyl)methoxy group, a (3,5-dimethylphenyl)methoxy group, a (2,3,4-trimethylphenyl)methoxy group, a (2,3,5-trimethylphenyl)methoxy group, a

(2,3,6-trimethylphenyl)methoxy group, a
(2,4,5-trimethylphenyl)methoxy group, a
(2,4,6-trimethylphenyl)methoxy group, a
(3,4,5-trimethylphenyl)methoxy group, a
5 (2,3,4,5-tetramethylphenyl)methoxy group, a
(2,3,5,6-tetramethylphenyl)methoxy group, a
(pentamethylphenyl)methoxy group, an (ethylphenyl)methoxy
group, a (n-propylphenyl)methoxy group, an
(isopropylphenyl)methoxy group, a (n-butylphenyl)methoxy
10 group, a (sec-butylphenyl)methoxy group, a
(tert-butylphenyl)methoxy group, a (n-hexylphenyl)methoxy
group, a (n-octylphenyl)methoxy group, a
(n-decylphenyl)methoxy group, a (n-tetradecylphenyl)methoxy
group, a naphthylmethoxy group and an anthracenylmethoxy group.
15 Preferred is a benzyloxy group.

Specific examples of the organoaluminum compound
represented by the formula [6] are trialkylaluminums such as
trimethylaluminum, triethylaluminum, tri-n-propylaluminum,
tri-n-butylaluminum, triisobutylaluminum,
20 tri-n-hexylaluminum and tri-n-octylaluminum; dialkylaluminum
chlorides such as dimethylaluminum chloride, diethylaluminum
chloride, di-n-propylaluminum chloride, di-n-butylaluminum
chloride, diisobutylaluminum chloride and di-n-hexylaluminum
chloride; alkylaluminum dichlorides such as methylaluminum
25 dichloride, ethylaluminum dichloride, n-propylaluminum
dichloride, n-butylaluminum dichloride, isobutylaluminum
dichloride and n-hexylaluminum dichloride; dialkylaluminum
hydrides such as dimethylaluminum hydride, diethylaluminum
hydride, di-n-propylaluminum hydride, di-n-butylaluminum

hydride, diisobutylaluminum hydride and di-n-hexylaluminum hydride; trialkoxyaluminums such as trimethoxyaluminum, triethoxyaluminum and tri(tert-butoxy)aluminum; alkyl dialkoxyaluminums such as methy(dimethoxy)aluminum, 5 methyl(diethoxy)aluminum and methyl(di-tert-butoxy)aluminum; dialkylalkoxyaluminums such as dimethy(methoxy)aluminum, dimethyl(ethoxy)aluminum and dimethyl(tert-butoxy)aluminum; triaryloxyaluminums such as triphenoxyaluminum, tris(2,6-diisopropylphenoxy)aluminum 10 and tris(2,6-diphenylphenoxy)aluminum; alkyl diaryloxyaluminums such as methyl(diphenoxy)aluminum, methylbis(2,6-diisopropylphenoxy)aluminum and methylbis(2,6-diphenylphenoxy)aluminum; and dialkylaryloxyaluminums such as dimethyl(phenoxy)aluminum, 15 dimethyl (2,6-diisopropylphenoxy)aluminum and dimethyl (2,6-diphenylphenoxy)aluminum.

Among these, preferred are trialkylaluminums, more preferred are trimethylaluminum, triethylaluminum, tri-n-butylaluminum, triisobutylaluminum, 20 tri-n-hexylaluminum and tri-n-octylaluminum, and particularly preferred are triisobutylaluminum and tri-n-octylaluminum.

These organoaluminum compounds may be used singly or in combination of two or more.

The component (B) is used in an amount of usually from 25 1×10^{-6} to 1×10^{-3} mol, and preferably from 5×10^{-6} to 5×10^{-4} mol per g of the component (A). The component (C) is used in an amount of preferably from 0.01 to 10,000, more preferably from 0.1 to 5,000, and the most preferably from 1 to 2,000 in terms of a molar ratio ((C)/(B)), namely in terms of the aluminum

atom in the organoaluminum compound of the compound (c) to the transition metal atom in the transition metal compound of the component (B).

As the catalyst for addition polymerization in accordance
5 with the present invention, a reaction product obtained in advance by contacting the component (A) and the component (B) and optionally the component (C) with one another may be used, or these components may be used in a manner of separately feeding in a polymerization reaction apparatus. When the components
10 (A), (B) and (C) are used, optional two components selected therefrom may be contacted in advance with each other, followed by contact of the remaining one component.

A method for supplying respective catalyst components to the reactor is also not particularly limited. There can be
15 applied a method comprising supplying respective components in each solid state, or in a solution, suspension or slurry state obtained using a hydrocarbon solvent, provided that any ingredient capable of de-activating the catalyst components such as water and oxygen has been sufficiently eliminated from
20 the hydrocarbon solvent. As a solvent used, there are listed aliphatic hydrocarbon solvents such as butane, pentane, hexane, heptane and octane, aromatic hydrocarbon solvents such as benzene and toluene, and a halogenated hydrocarbon solvents such as methylene chloride, and aliphatic hydrocarbon solvents
25 and aromatic hydrocarbon solvents are preferred.

When the catalyst components are supplied in their solution, suspension or slurry state, a concentration of the component(A) is usually from 0.01 to 1000 g/l, and preferably from 0.1 to 500 g/l. A concentration of the component(C) is

usually from 0.0001 to 100 mol/l, and preferably from 0.01 to 10 mol/l in terms of Al atom. A concentration of the component (B) is usually from 0.0001 to 1000 mmol/l, and preferably from 0.01 to 50 mmol/l in terms of the transition metal atom.

5 The polymerization process is not particularly limited, and it is permitted to apply a gas phase polymerization carried out in a gaseous monomer or a solution polymerization or slurry polymerization using a solvent. A solvent used for the solution polymerization or the slurry polymerization includes an
10 aliphatic hydrocarbon solvent such as butane, hexane, pentane, heptane and octane; an aromatic hydrocarbon solvent such as benzene and toluene; and a halogenated hydrocarbon solvent such as methylene chloride. Alternatively, it is possible to use an olefin itself as a solvent (bulk polymerization). As the
15 polymerization process, any of a batch polymerization and a continuous polymerization can be applied. It is permitted to carry out the polymerization dividing into two or more steps different from one another in their reaction conditions. A polymerization time can be appropriately determined according
20 to a kind of the desired olefin polymer and a reaction apparatus, and it is permitted to adopt a period of time of from 1 minute to 20 hours.

 The present invention can be particularly suitably applied to a polymerization accompanied by the formation of addition
25 polymer particles (for example, a slurry polymerization, a gas phase polymerization and a bulk polymerization).

 The slurry polymerization may be carried out in a conventional slurry polymerization manner and condition, but it is not limited thereto. According to a preferred slurry

polymerization, a monomer (and a comonomer), a material to be supplied, a diluent and the like are, if desired continuously added, and a continuous type reactor is used, so that a produced polymer is continuously or at least periodically taken out.

5 Further, there can be applied a means using a loop reactor or a means using a stirring reactor. In addition, more than one stirring reactor, which may be different in a reactor or in a reaction condition, may be combined in series, in parallel or in series and parallel.

10 As the diluent, there can be used an inert diluent (medium) such as paraffin, cycloparaffin and aromatic hydrocarbons. A temperature of the polymerization reactor or a reaction zone is usually from about 0 to about 150°C, and preferably from 30 to 100°C. A pressure can be varied within a range of from
15 about 0.1 to about 10 MPa, and preferably from 0.5 to 5 MPa. It is permitted to apply a pressure, under which a monomer and a comonomer are contacted with each other while maintaining the catalyst in a suspended state, and the medium and at least a part of the monomer and comonomer in a solution phase.
20 Accordingly, the medium, temperature and pressure may be selected so as to produce the addition polymer in a solid particle form and recover it in that form.

A molecular weight of the addition polymer can be controlled by known manners, for example, by controlling a
25 temperature of a reaction zone or introducing hydrogen.

The catalyst components and a monomer (and a comonomer) can be fed into a reactor or a reaction zone in an arbitrary order according to a conventional manner. For example, the catalyst components and a monomer (and a comonomer) are fed

into a reaction zone at the same time or one after the other. If desired, the catalyst components and a monomer (and a comonomer) can be subjected to pre-contact in an inert atmosphere before their contact.

5 The gas phase polymerization may be carried out in a conventional gas phase polymerization manner and condition, but it is not limited thereto. As a gas phase polymerization apparatus, a fluidized bed reactor, preferably a fluidized bed reactor having an expansion can be used. A reaction apparatus
10 equipped with a stirring blade in its reaction zone may also be used without any problem.

 Respective components can be fed into a polymerization zone in a water-free state using an inert gas such as nitrogen or argon, or hydrogen or ethylene, or in feeding, respective
15 components can be dissolved or diluted in a solvent to form a solution or a slurry. The catalyst components may be fed independently, or in feeding, arbitrarily selected catalyst components may be contacted in advance with one another in an arbitrary order.

20 With respect to polymerization conditions, a temperature is lower than that at which the polymer is melted, preferably from 0 to 150°C, and particularly preferably from 30 to 100°C. Furthermore, for the purpose of controlling the melt flow of a final product, it is permitted to add hydrogen as a molecular
25 weight regulator. In addition, it is permitted that an inert gas coexists in the mixed gas during polymerization.

 In the present invention, a pre-polymerization as mentioned below may be carried out before carrying out the above-mentioned polymerization (real polymerization).

The pre-polymerization can be carried out by feeding a small amount of an olefin in the presence of the modified particle (A) and the transition metal compound (B), or further in the presence of the organoaluminum compound (A). It is recommendable
5 to carry out in a slurry state. Examples of a solvent used for formation of the slurry are inert hydrocarbons such as propane, butane, isobutane, pentane, isopentane, hexane, heptane, octane, cyclohexane, benzene and toluene. Further, in forming the slurry, it is permitted to use a liquefied olefin in place
10 of a part or the whole of the inert hydrocarbon.

In the pre-polymerization, an amount of the organoaluminum compound (C) can be determined within a wide range of from 0.5 to 700 mol per mol of the transition metal compound (B). Preferable is from 0.8 to 500 mol per mol thereof,
15 and particularly preferable is from 1 to 200 mol per mol thereof.

An amount of the olefin to be subjected to the pre-polymerization is usually from 0.01 to 1000 g per g of the modified particle, preferably from 0.05 to 500 g per g thereof, and particularly preferably from 0.1 to 200 g per g thereof.

20 In the pre-polymerization, a slurry concentration is preferably from 0.1 to 50 g-above-mentioned modified particle/l-solvent, and particularly preferably from 0.5 to 20 g-the above-mentioned modified particle/l-solvent. A pre-polymerization temperature is preferably from -20 to 100°C, and particularly preferably from 0 to 80°C. A partial pressure
25 of the olefin in the gas phase during the pre-polymerization is preferably from 0.001 to 2 MPa, and particularly preferably from 0.01 to 1 MPa, excepting an olefin which is liquid under the pressure and temperature conditions of pre-polymerization.

Further, a pre-polymerization time is not particularly limited, and usually from 2 minutes to 15 hours.

In carrying out the pre-polymerization, as a process for supplying the modified particle (A), transition metal compound (B), organoaluminum compound (C) and olefin, there can be applied any process of a process comprising contacting the modified particle (A), the transition metal compound (B) and optionally the organoaluminum compound (C), and thereafter supplying the olefin; a process comprising contacting the modified particle (A), the transition metal compound (B) and the olefin, and thereafter supplying the organoaluminum compound (C); a process comprising contacting the organoaluminum compound (C) and the transition metal compound (B) in the presence of the olefin, and thereafter supplying the modified particle (A), and the like. Further, as a supply method of the olefin, any of a method comprising supplying the olefin in order while keeping the pre-determined pressure of the polymerization zone, and a method comprising supplying all the pre-determined amount of the olefin in the first place can be applied. It is also permitted to add a chain transfer agent such as hydrogen to regulate a molecular weight of the polymer obtained.

In the present invention, that obtained by the pre-polymerization as mentioned above can be used as a catalyst component or a catalyst. The pre-polymerized catalyst component in accordance with the present invention includes a pre-polymerized catalyst component for addition polymerization obtained by pre-polymerizing an olefin in the presence of the catalyst for addition polymerization obtained by contacting the above-mentioned modified particle (A) and the transition

metal compound of the Groups 3 to 11 or lanthanoide series with each other, and a pre-polymerized catalyst component for addition polymerization obtained by pre-polymerizing an olefin in the presence of the catalyst for addition polymerization
5 obtained by contacting the above-mentioned modified particle (A), the transition metal compound of the Groups 3 to 11 or lanthanoide series and the organoaluminum compound (C) with one another. The pre-polymerized catalyst in accordance with the present invention includes a catalyst for addition
10 polymerization obtained by pre-polymerizing an olefin in the presence of the catalyst for addition polymerization obtained by contacting the above-mentioned modified particle (A) and the transition metal compound of the Groups 3 to 11 or lanthanoide series with each other, and a catalyst for addition
15 polymerization obtained by pre-polymerizing an olefin in the presence of the catalyst for addition polymerization obtained by contacting the above-mentioned modified particle (A), the transition metal compound of the Groups 3 to 11 or lanthanoide series and the organoaluminum compound (C) with one another.
20 The catalyst obtained using said pre-polymerized catalyst component for addition polymerization in accordance with the present invention includes a catalyst for addition polymerization obtained by contacting said pre-polymerized catalyst component for addition polymerization and the
25 organoaluminum compound (C) with each other.

The production process of an addition polymer of the present invention is a process for producing an addition polymer, in which an addition polymerizable monomer is polymerized in the presence of the above-described catalyst for addition

polymerization of the present invention. Examples of the monomer used in the polymerization are olefins having 2 to 20 carbon atoms, diolefins, cyclic olefins, alkenyl aromatic hydrocarbons and polar monomers. Two or more kinds of the monomer
5 may be used at the same time. It is permitted to use two or more monomers at the same time.

Specific examples thereof are olefins such as ethylene, propylene, 1-butene, 1-pentene, 4-methyl-1-pentene, 5-methyl-1-hexene, 1-hexene, 1-heptene, 1-octene, 1-nonene and
10 1-decene; diolefins such as 1,5-hexadiene, 1,4-hexadiene, 1,4-pentadiene, 1,7-octadiene, 1,8-nonadiene, 1,9-decadiene, 4-methyl-1,4-hexadiene, 5-methyl-1,4-hexadiene, 7-methyl-1,6-octadiene, 5-ethylidene-2-norbornene, dicyclopentadiene, 5-vinyl-2-norbornene, 5-methyl-2-
15 norbornene, norbornadiene, 5-methylene-2-norbornene, 1,5-cyclooctadiene, 5,8-endomethylenehexahydronaphthalene, 1,3-butadiene, isoprene, 1,3-hexadiene, 1,3-octadiene, 1,3-cyclooctadiene and 1,3-cyclohexadiene; cyclic olefins such as norbornene, 5-methyl-2-norbornene, 5-ethyl-2-norbornene,
20 5-butyl-2-norbornene, 5-phenyl-2-norbornene, 5-benzyl-2-norbornene, tetracyclododecene, tricyclodecene, tricycloundecene, pentacyclopentadecene, pentacyclohexadecene, 8-methyltetracyclododecene, 8-ethyltetracyclododecene, 5-acetyl-2-norbornene,
25 5-acetyloxy-2-norbornene, 5-methoxycarbonyl-2-norbornene, 5-ethoxycarbonyl-2-norbornene, 5-methyl-5-methoxycarbonyl-2-norbornene, 5-cyano-2-norbornene, 8-methoxycarbonyltetracyclododecene, 8-methyl-8-tetracyclododecene and

8-cyanotetracyclododecene; alkenylbenzenes such as styrene, 2-phenylpropylene, 2-phenylbutene and 3-phenylpropylene; alkylstyrenes such as p-methylstyrene, m-methylstyrene, o-methylstyrene, p-ethylstyrene, m-ethylstyrene, 5 o-ethylstyrene, 2,4-dimethylstyrene, 2,5-dimethylstyrene, 3,4-dimethylstyrene, 3,5-dimethylstyrene, 3-methyl-5-ethylstyrene, 1,1-diphenylethylene. p-tert-butylstyrene and p-sec-butylstyrene; alkenyl aromatic hydrocarbons such as bisalkenylbenzenes including 10 divinylbenzene and alkenylnaphthalenes including 1-vinylnaphthalene; and polar monomers such as α , β -unsaturated carboxylic acids such as acrylic acid, methacrylic acid, fumaric acid, maleic anhydride, itaconic acid, itaconic anhydride and bicyclo(2,2,1)-5-heptene-2,3-dicarboxylic acid 15 and their salts of metals such as sodium, potassium, lithium, zinc, magnesium and calcium, α , β -unsaturated carboxylic acid esters such as methyl acrylate, ethyl acrylate, n-propyl acrylate, isopropyl acrylate, tert-butyl acrylate, 2-ethylhexyl acrylate, methylmethacrylate, ethylmethacrylate, 20 n-propyl methacrylate, isopropyl methacrylate, n-butyl methacrylate and isobutyl methacrylate, unsaturated dicarboxylic acids such as maleic acid and itaconic acid, vinyl esters such as vinyl acetate, vinyl propionate, vinyl caproate, vinyl caprate, vinyl laurate, vinyl stearate and vinyl 25 trifluoroacetate, and unsaturated carboxylic acid glycidyl esters such as glycidyl acrylate, glycidyl methacrylate and monoglycidyl itaconate.

The present invention can be applied to homopolymerization or copolymerization of these monomers.

Examples of copolymer-constituting monomers are ethylene-propylene, ethylene-1-butene, ethylene-1-hexene, ethylene-1-octene, ethylene-vinylcyclohexane and propylene-1-butene, ethylene-propylene-1-butene, 5 ethylene-propylene-1-hexene and the like, but the present invention should not be limited thereto.

The catalyst for addition polymerization of the present invention is particularly suitable for a catalyst for polymerizing an olefin, and it is preferably used for a process 10 for producing an olefin polymer. Particularly preferable example of the olefin polymer is an ethylene- α -olefin copolymer obtained by polymerizing a mixture of ethylene and the α -olefin. Among them, preferable is an ethylene- α -olefin copolymer having a polyethylene crystal structure. Herein, preferable is an α -olefin having 3 to 8 carbon atoms such as 1-butene, 1-hexene 15 and 1-octene.

EXAMPLE

The present invention is illustrated in more detail with 20 reference to Examples and Comparative Examples, but the present invention is not limited thereto. Measurement values of respective items in Examples were obtained by the following methods.

(1) Content of α -olefin unit in copolymer

25 The content of a repeating unit derived from the α -olefin in the polymer obtained was determined from IR absorption spectrum, and was expressed in terms of a short chain branch number (SCB) per 1000 carbon atoms. In addition, the measurement and calculation were carried out using characteristic

absorption derived from the α -olefin according to a method described in "Die Macromolekulare Chemie, 177, 449 (1976) McRae, M.A., Madams, W.F.". The IR spectrum was measured using an IR spectrophotometer (FT-IR 7300, manufactured by Japan

5 Spectroscopic Co., Ltd.).

(2) Intrinsic viscosity $[\eta]$: It was measured in a tetralin solution at 135°C using Ubbelohde viscometer. (Unit: dl/g)

(3) Measurement of ^{13}C -NMR

In the measurement of ^{13}C -NMR, JNM-EX270 (67.5 MHz, ^{13}C)
10 (manufactured by JOEL) was used. The measurement was carried out at room temperature using a deuterated solvent described in Examples.

(4) Molecular weight and molecular weight distribution :

It was measured under the conditions described below
15 according to gel permeation chromatography (GPC). A calibration curve was prepared using a standard polystyrene. The molecular weight distribution was represented by a ratio (Mw/Mn) of a weight average molecular weight (Mw) to a number average molecular weight (Mn).

20 Measurement machine: 150C type, manufactured by Milipore Waters Co.

Column: TSK-GEL GMH-HT (7.5 × 600) : 2 columns

Measurement temperature: 140°C

Solvent: ortho-dichlorobenzene

25 Measurement concentration: 5mg/5ml

(5) Melt flow rate (MFR)

It was measured under a load of 21.18N at a temperature of 190°C according to JIS K7210-1995. (Unit: g/10 minutes)

(6) Melt flow rate ratio (MFRR)

Melt flow rates under a load of 21.18N at a temperature of 190°C and under a load of 211.82N at a temperature of 190°C according to JIS K7210-1995 were measured as MFR and MFR2, respectively, and a value (MFR2/MFR) in which MFR2 was divided
5 by MFR, was defined as melt flow rate ratio(MFRR).

(7)Swelling ratio (SR)

A strand was extruded under load of 21.18N at a temperature of 190°C using a melt flow measurement apparatus specified in JIS K7210-1995. The diameter (d(mm)) of the strand measured
10 was divided by a diameter (d_0 (mm)=2.095) of an orifice of the apparatus, and the value (d/d_0) was defined as swelling ratio(SR).

(8)Melting point (mp)

It was measured using a differential scanning calorimeter
15 (manufactured by Seiko Instrument Inc., SSC-5200) under the following conditions:

Conditioning:

The temperature was raised from 40 to 150°C at a rate of 10°C/min., kept at 150°C for 5 minutes, lowered from 150 to 40
20 at a rate of 5°C/min. and then kept at at 40°C for 10 minutes.

Measurement of mp:

After the conditioning, the temperature was immediately raised from 40 to 160 °C at a rate of 5°C/min.

Example 1

25 (1) Synthesis of intermediate

In a 300 ml four necked flask purged with argon, 9.88 g (22.4 mmol) of triphenylbismuth and 100 ml of toluene were introduced and stirred at room temperature. To the mixture was dropped a solution of 12.6 g (68.5 mmol) of pentafluorophenol

dissolve with 100 ml of toluene. After completion of dropping, the mixture was stirred at room temperature for 15.5 hours. Thereafter, the reaction was carried out for 4 hours under reflux of toluene, for 18 hours at room temperature, for 7 hours under
5 of toluene, and then for 17 hours at room temperature in this order. A yellow needle-like crystal was separated by filtration, and dried under reduced pressure at room temperature to obtain 12.6 g of a intermediate.

(2) Synthesis of component (A)

10 In a 50 ml four necked flask purged with argon, 1.54 g of the intermediate obtained in the Example 1(1) and 40 ml of toluene were charged and stirred at room temperature. To this, 0.73 g of silica (Sylopol 948, manufactured by Davison Co., Ltd.; A median particle diameter = 55 μ m; pore volume = 1.66
15 ml/g; specific surface area = 309 m²/g) which had been heat-treated at 300°C under a nitrogen stream, was added, the mixture was heated to 80 °C and stirred for 2 hours. After collecting a solid by filtration, the solid was washed four times with each 20 ml of toluene, then once with 20 ml of hexane,
20 and then dried under reduced pressure at room temperature thereby obtaining a component (A). Elementary analysis revealed Bi = 0.48 mmol/g, and F = 4.0 mmol/g.

(3) Polymerization

25 A 3 l-inner volume autoclave equipped with a stirrer, which had been dried under reduced pressure and thereafter purged with argon, was made vacuum, 0.49 Vol % of hydrogen, 700 g of butane as a solvent and 50 g of 1-butene as a comonomer were fed therein, and then a temperature of the autoclave was raised to 70°C. Thereafter, ethylene was fed therein to obtain a partial

pressure of 1.6 MPa, and the system was stabilized. To the resultant was added 0.9 mmol of triisobutylaluminum, successively, 0.5 μ mol of ethylenebis(indenyl)zirconium dichloride, and then 17.2 mg of the component (A) obtained in the above (2) were added thereto to initiate polymerization. Polymerization was carried out for 60 minutes. As a polymerization result, 35 g of an ethylene/1-butene copolymer was obtained. As polymerization results, polymerization activity was 2000 g/g-carrier/h, SCB was 15.15, MFR was 0.93 g/10 min., MFRR was 91.40, and SR was 1.25.

Example 2

(1) Polymerization

In a 0.4 l-inner volume autoclave equipped with a stirrer, which had been dried under reduced pressure and thereafter purged with argon, 10 ml of 1-hexene as a comonomer and 190 ml of hexane as a solvent were charged, the reactor was heated to 70°C. After heating, ethylene was fed therein while keeping a partial pressure of 0.6 MPa. After the system was stabilized, to the resultant was added 0.25 mmol of triisobutylaluminum, successively, 1 μ mol of ethylenebis(indenyl)zirconium dichloride, and then 30.4 mg of the component (A) obtained in Example 1 (2) were added thereto to initiate polymerization. Polymerization was carried out for 30 minutes. As a polymerization result, 22.4 g of an ethylene/1-hexene copolymer was obtained. Polymerization activity was 1500 g/g-carrier/h and 45 kg/ mmol-Zr/h. $M_w = 58,000$, $M_w/M_n = 1.9$, SCB = 36.0.

Example 3

(1) Synthesis of intermediate

In a 2000 ml four necked flask purged with argon, 101 g (230 mmol) of triphenylbismuth and 500 ml of toluene were introduced and stirred at room temperature. To the mixture was
5 dropped 345 ml of a toluene solution (concentration of pentafluorophenol: 2 mmol/ml, amount of pentafluorophenol: 690 mmol) of pentafluorophenol. After completion of dropping, the reaction was carried out for 11 hours under reflux of toluene. A yellow needle-like crystal was separated by filtration, and
10 dried under reduced pressure at room temperature to obtain 171 g of a intermediate. From an elementary analysis, Bi and F contents were 1.2 mmol/g and 15 mmol/g, respectively.

(2) Synthesis of component (A)

In a 1000 ml four necked flask purged with argon, 17.7 g (23.4
15 mmol) of the intermediate obtained in the Example 3(1) and 300 ml of toluene were charged and stirred at room temperature. To this, 21.1 g of silica (Sylopol 948, manufactured by Davison Co., Ltd.; A median particle diameter = 55 μ m; pore volume = 1.7 ml/g; specific surface area = 306 m²/g) which had been
20 heat-treated at 300°C under a nitrogen stream, and 30 ml of toluene were added, the mixture was heated to 80 °C and stirred for 2 hours. After collecting a solid by filtration, the solid was washed four times with each 100 ml of toluene, then once with 100 ml of hexane, and then dried under reduced pressure
25 at room temperature to obtain 27.5 g of a component (A). Elementary analysis revealed Bi = 0.48 mmol/g, and F = 3.3 mmol/g.

(3) Polymerization

To a 0.4 l-inner volume autoclave equipped with a stirrer, which had been dried under reduced pressure and thereafter purged

with argon, 10 ml of 1-hexene as a comonomer and 190 ml of hexane as a solvent were charged, and then the autoclave was heated to 70°C. After the heating, ethylene was fed therein to obtain a partial pressure of 0.6 MPa, and after the system was
5 stabilized, 0.25 mmol of triisobutylaluminum was charged therein, successively, 0.3 μ mol of ethylenebis(indenyl)zirconium dichloride, further 9.1 mg of the component (A) obtained in the above (2) were added thereto to initiate polymerization. Polymerization was carried out for
10 30 minutes. As polymerization results, 16.1 g of an ethylene/1-hexene copolymer was obtained. A polymerization activity was 3500 g/g-carrier/h and 110 kg/mmol-Zr/h. $M_w = 160,000$, $M_w/M_n = 3.8$, $\eta = 1.65$, and SCB was 18.81.

Comparative Example 1

15 (1)

Synthesis was carried out according to Example 1(2) except that 1.16 g of triphenyl bismuth was used in stead of 1.54 g of the intermediate obtained in Example 1(1), and the amount of silica was changed to 1.10 g. As a result, 0.79 g of a white
20 solid was obtained.

(2) Polymerization

In a 0.4 l-inner volume autoclave equipped with a stirrer, which had been dried under reduced pressure and thereafter purged with argon, 10 ml of 1-hexene as a comonomer and 190 ml of hexane
25 as a solvent were charged, the reactor was heated to 70°C. After heating, ethylene was fed therein while keeping a partial pressure of 0.6 MPa. After the system was stabilized, to the resultant was added 0.25 mmol of triisobutylaluminum, successively, 1 μ mol of ethylenebis(indenyl)zirconium

dichloride, and then 22.9 mg of the white solid obtained in Comparative Example 1(1) were added thereto to initiate polymerization. Polymerization was carried out for 30 minutes. As a polymerization result, a trace amount of a polymer was
5 obtained.


Example 4

(1) Synthesis of dimethylsilylene(η^5 -tetramethylcyclopentadienyl) (3-tert-butyl-5-methyl-2-phenoxy) titanium dimethoxide

10 In a Schlenk tube, 0.131g (4.1mmol) of methyl alcohol was dissolved in 10ml of anhydrous diethyl ether and a diethyl ether solution (3.9ml, 4.1mmol) of methyllithium having a concentration of 1.05 mol/L was added dropwise at -78°C thereto. The resulting mixture was heated to 20°C , the formation of lithium
15 methoxide was confirmed by gas generation, and the resulting reaction solution was again cooled to -78°C . Into the reaction solution, 20ml of an anhydrous diethyl ether suspension liquid of 0.919g (2.0mmol) of dimethylsilylene(η^5 -tetramethylcyclopentadienyl) (3-tert-butyl-5-methyl-2-phenoxy) titanium dichloride which was previously prepared in
20 another Schlenk tube was transferred, and then, the resulting reaction mixture was gradually heated to room temperature to obtain a reaction solution. After concentrating the reaction solution, 20ml of toluene was added and an insoluble product
25 was separated by filtration. The filtrate was concentrated to obtain dimethylsilylene(η^5 -tetramethylcyclopentadienyl) (3-tert-butyl-5-methyl-2-phenoxy) titanium dimethoxide represented by the structural formula described below of yellow crystals (0.86g, 95%) (hereinafter, referred to as "Compound

A").

$^1\text{H-NMR}$ (270MHz, C_6D_6); δ 7.26 (m, 2H), 4.13(s, 6H), 2.33 (s, 3H), 1.97(s, 6H), 1.89(s, 6H), 1.59(s, 9H), 0.55(s, 6H)



5 (2) Polymerization

To a 0.4 l-inner volume autoclave equipped with a stirrer, which had been dried under reduced pressure and thereafter purged with argon, 2ml of 1-hexene as a comonomer and 198ml of cyclohexane as a solvent were charged thereto, and the temperature of the reactor was raised to 70°C. After raising the temperature, ethylene was fed while adjusting its pressure at 0.6 Mpa. After the system was stabilized, 0.25 mmol of triisobutylaluminum was charged, successively 1ml of a toluene solution in which a mixture of the compound A and triisobutylaluminum was dissolved (the concentration of the compound A is 1 μ mol/ml, the concentration of triisobutylaluminum is 50 μ mol/ml, and the molar ratio of Al to Ti was adjusted to 50) (namely, 1 μ mol of the compound A and 50 μ mol of triisobutylaluminum) were charged, and further 43.0 mg of the component A obtained in Example 1(2) was charged to initiate polymerization. Polymerization was carried out for 30 minutes. As a result of the polymerization, 1.79 g of an ethylene-1-hexene copolymer was obtained. A polymerization

activity was 83 g/g-carrier/h, and 3.6 kg/mmol-Ti/h, Mw was 440,000, Mw/Mn was 2.1, $[\eta]$ was 4.55dl/g, and SCB was 19.34.

Example 5

5 (1) Synthesis of intermediate

In a 500 ml four necked flask purged with argon, 17.2 g (39.1 mmol) of triphenylbismuth and 175 ml of toluene were introduced and stirred at room temperature. To the mixture was dropped 50 ml of a toluene solution in which 22.0g(119 mmol) of pentafluorophenol was dissolved. After completion of dropping, the reaction was carried out for 8 hours under reflux of toluene, for 15 hours at room temperature and 4 hours under reflux of toluene. A yellow needle-like crystal was separated by filtration, and dried under reduced pressure at room temperature to obtain 28.2 g of an intermediate.

(2) Synthesis of component (A)

In a 100 ml four necked flask purged with argon, 2.48g of the intermediate obtained in the Example 5(1) and 40 ml of toluene were charged and stirred at room temperature. To this, 3.11 g of silica (Sylopol 948, manufactured by Davison Co., Ltd.; A median particle diameter = 55 μ m; pore volume =1.66 ml/g; specific surface area = 309 m²/g) which had been heat-treated at 300°C under a nitrogen stream, and 5ml of toluene were added, the mixture was heated to 80 °C and stirred for 2 hours. After collecting a solid by filtration, the solid was washed four times with each 30 ml of toluene, then once with 30 ml of hexane, and then dried under reduced pressure at room temperature to obtain 3.84g of a component(A). Elementary analysis revealed Bi = 0.53 mmol/g, and F = 3.2 mmol/g.

(3) Polymerization

To a 0.4 l-inner volume autoclave equipped with a stirrer, which had been dried under reduced pressure and thereafter purged with argon, 15 ml of 1-hexene as a comonomer and 185 ml of cyclohexane as a solvent were charged, and then the autoclave was heated to 180°C. After the heating, ethylene was fed therein to obtain a partial pressure of 2.5 MPa, and after the system was stabilized, 0.3 mmol of triisobutylaluminum was charged, successively 1ml of a toluene solution in which a mixture of the compound A and triisobutylaluminum was dissolved (the concentration of the compound A is 0.5 μ mol/ml, the concentration of triisobutylaluminum is 25 μ mol/ml, and the molar ratio of Al to Ti was adjusted to 50) (namely, 0.5 μ mol of the compound A and 25 μ mol of triisobutylaluminum) were charged, and further 126 mg of the component A obtained in Example 5(2) was charged to initiate polymerization. Polymerization was carried out for 2 minutes. As a result of the polymerization, 1.41 g of an ethylene-1-hexene copolymer was obtained. A polymerization activity was 340 g/g-carrier/h, and 85 kg/mmol-Ti/h, Mw was 100000, Mw/Mn was 1.9, $[\eta]$ was 1.46 dl/g, and mp was 81.4 °C.

As mentioned above in detail, according to the present invention, there are provided a modified particle which can form a catalyst for addition polymerization exhibiting a high polymerization activity by using as a co-catalyst component for activation (catalyst component); a catalyst component for addition polymerization composed of the modified particle; a catalyst for addition polymerization prepared by using the

catalyst component; and a process for producing an addition polymer efficiently using the catalyst for addition polymerization.